

TEST REPORT

Report No.: YW202607015201E

Date: Aug. 13, 2026

Page: 1 / 13

Applicant : Mid Ocean Brands B.V.
Address : Unit 711-716, 7/F., Tower A, 83 King Lam Street
Cheung Sha Wan, Kowloon, Hong Kong

Below information was/were submitted and identified by the applicant:

Product Name : Stainless steel hip flask
Model : MO6356
Main material : /
Manufacturer info. : /
Supplier info. : 107961
Buyer info. : /
Country of Destination : /
Country of Origin : /

Sample Received : Jul. 10, 2026
Test Period : Jul. 10, 2026 - Aug. 12, 2026
Test Requested : Refer to next pages
Test Method(s) : Refer to next pages
Test Result(s) : Refer to next pages

Tested By: Lyra Jin
Lyra Jin

Reviewed By: Ally Lu
Ally Lu

Approved By:



TEST REPORT

Report No.: YW202607015201E

Date: Aug. 13, 2026

Page: 2 / 13

RESULT SUMMARY

As requested by the client, according to Commission Regulation (EU) No 10/2011 and its subsequent amendment (EU) 2020/1245, (EU) 2024/3190 on plastic materials and articles intended to come into contact with foodstuffs, EU Resolution CM/Res(2020)9, Technical Guide on Metals and Alloys used in food contact materials and articles of the 2nd edition in 2024, General Requirement (Article 3) in EU Regulation (EC) No.1935/2004 to do the following test items:

Test Item(s)	Conclusion
1. Overall migration on Plastic	PASS
2. Specific migration of heavy metals on Plastic	PASS
3. Specific migration of Primary Aromatic Amines (PAA) on Plastic	PASS
4. Bisphenol A (BPA) content-(EU) 2024/3190	PASS
5. Extractable Heavy Metals on Metal part	PASS
6. Lead (Pb) content-Regulation (EC) No.1907/2006, REACH Annex XVII (entry 63)	PASS
7. Cadmium (Cd) content-Regulation (EC) No.1907/2006, REACH Annex XVII (entry 23)	PASS
8. Phthalates content-Regulation (EC) No.1907/2006, REACH Annex XVII (entry 51&52)	PASS
9. Polycyclic Aromatic Hydrocarbons (PAHs) content-Regulation (EC) No.1907/2006, REACH Annex XVII (entry 50)	PASS
10. PCP content according to Regulation (EU) 2019/1021 of the European Parliament and of the Council of 20 June 2019 on persistent organic pollutants (POPs) and its subsequent amendments regulation.	PASS
11. Formaldehyde release-Regulation (EC) No.1907/2006, REACH Annex XVII (entry 77)	PASS

TEST REPORT

Report No.: YW202607015201E

Date: Aug. 13, 2026

Page: 3 / 13

TEST PART DESCRIPTION

- 1# White plastic gasket
- 2# Bamboo shell
- 3# Silver metal inner wall
- 4# Silver metal lid
- 5# Silver electroplated hinge
- 6# White plastic hinge substrate

TEST RESULT(S)

1. Overall migration test

Test method:

EN 1186-1:2002 for guide to the selection of conditions and test methods for overall migration;

EN 1186-3:2022 for overall migration in evaporable simulants;

Test Parameter	Unit	MDL	Test Results		Permissible Limit
			1#	1#	
Test simulant			50% ethanol	3% acetic acid	---
Test condition			0.5 hour at 40°C	0.5 hour at 40°C	---
Surface area/volume(dm ² /ml)			1/100	1/100	---
Overall migration, 1 st	mg/dm ²	3.0	N.D.	N.D.	---
Overall migration, 2 nd	mg/dm ²	3.0	N.D.	N.D.	---
Overall migration, 3 rd	mg/dm ²	3.0	N.D.	N.D.	≤10
Comment(s)*			PASS	PASS	---

***** To be continued *****

TEST REPORT

Report No.: YW202607015201E

Date: Aug. 13, 2026

Page: 4 / 13

2. Specific migration of heavy metals

Test method: With reference to EN 13130-1:2004, followed by analysis using ICP-OES and ICP-MS.

Test Parameter	Unit	MDL	Test Results			Permissible Limit
			1#, 1 st	1#, 2 nd	1#, 3 rd	
Test simulant			3% acetic acid			---
Test condition			1 hour at 40°C			---
Surface area/volume(dm ² /ml)			1/167			---
Soluble Aluminum (Al)	mg/kg	0.1	N.D.	N.D.	N.D.	≤1.0
Soluble Antimony (Sb)	mg/kg	0.01	N.D.	N.D.	N.D.	≤0.04
Soluble Arsenic (As)	mg/kg	0.01	N.D.	N.D.	N.D.	ND
Soluble Barium (Ba)	mg/kg	0.25	N.D.	N.D.	N.D.	≤1.0
Soluble Cadmium (Cd)	mg/kg	0.002	N.D.	N.D.	N.D.	ND
Soluble Chromium (Cr)	mg/kg	0.01	N.D.	N.D.	N.D.	ND
Soluble Cobalt (Co)	mg/kg	0.01	N.D.	N.D.	N.D.	≤0.05
Soluble Copper (Cu)	mg/kg	0.25	N.D.	N.D.	N.D.	≤5.0
Soluble Iron (Fe)	mg/kg	5.0	N.D.	N.D.	N.D.	≤48
Soluble Lead (Pb)	mg/kg	0.01	N.D.	N.D.	N.D.	ND
Soluble Lithium (Li)	mg/kg	0.1	N.D.	N.D.	N.D.	≤0.6
Soluble Manganese(Mn)	mg/kg	0.1	N.D.	N.D.	N.D.	≤0.6
Soluble Mercury (Hg)	mg/kg	0.01	N.D.	N.D.	N.D.	ND
Soluble Nickel (Ni)	mg/kg	0.01	N.D.	N.D.	N.D.	≤0.02
Soluble Zinc (Zn)	mg/kg	0.5	N.D.	N.D.	N.D.	≤5.0
Soluble Europium (Eu)	mg/kg	0.025	N.D.	N.D.	N.D.	Sum of Eu, Gd, La, Tb≤0.05
Soluble Gadolinium (Gd)	mg/kg	0.025	N.D.	N.D.	N.D.	
Soluble Lanthanum (La)	mg/kg	0.025	N.D.	N.D.	N.D.	
Soluble Terbium (Tb)	mg/kg	0.025	N.D.	N.D.	N.D.	
Comment(s)*	---	---	PASS			---

***** To be continued *****

TEST REPORT

Report No.: YW202607015201E

Date: Aug. 13, 2026

Page: 5 / 13

3. Specific migration of Primary Aromatic Amines (PAA)

Test method: With reference to EN 13130-1:2004, analysis was performed by LC-MS-MS.

Test Parameter	Unit	MDL	Test Results			Permissible Limit
			1#, 1 st	1#, 2 nd	1#, 3 rd	
Test simulant			3% acetic acid			---
Test condition			1 hour at 40°C			---
Surface area/volume(dm ² /ml)			1/167			---
4-Aminobiphenyl	mg/kg	0.002	N.D.	N.D.	N.D.	≤0.002
Benzidine	mg/kg	0.002	N.D.	N.D.	N.D.	≤0.002
4-Chloro-o-toluidine	mg/kg	0.002	N.D.	N.D.	N.D.	≤0.002
2-Naphthylamine	mg/kg	0.002	N.D.	N.D.	N.D.	≤0.002
O-Aminoazotoluene	mg/kg	0.002	N.D.	N.D.	N.D.	≤0.002
5-nitro-o-toluidine	mg/kg	0.002	N.D.	N.D.	N.D.	≤0.002
4-Chloroaniline	mg/kg	0.002	N.D.	N.D.	N.D.	≤0.002
4-methoxy-m-phenylenediamine	mg/kg	0.002	N.D.	N.D.	N.D.	≤0.002
4,4'-methylenedianiline	mg/kg	0.002	N.D.	N.D.	N.D.	≤0.002
3,3'-Dichlorobenzidine	mg/kg	0.002	N.D.	N.D.	N.D.	≤0.002
3,3'-Dimethoxybenzidine	mg/kg	0.002	N.D.	N.D.	N.D.	≤0.002
3,3'-Dimethylbenzidine	mg/kg	0.002	N.D.	N.D.	N.D.	≤0.002
4,4'-methylenedi-o-toluidine	mg/kg	0.002	N.D.	N.D.	N.D.	≤0.002
P-Cresidine	mg/kg	0.002	N.D.	N.D.	N.D.	≤0.002
4,4'-Methylene-bis-(2-Chloro-aniline)	mg/kg	0.002	N.D.	N.D.	N.D.	≤0.002
4,4'-oxydianiline	mg/kg	0.002	N.D.	N.D.	N.D.	≤0.002
4,4'-Thiodianiline	mg/kg	0.002	N.D.	N.D.	N.D.	≤0.002
O-Toluidine	mg/kg	0.002	N.D.	N.D.	N.D.	≤0.002
4-methyl-m-phenylenediamine	mg/kg	0.002	N.D.	N.D.	N.D.	≤0.002
2,4,5-Trimethylaniline	mg/kg	0.002	N.D.	N.D.	N.D.	≤0.002
4-Aminoazobenzene	mg/kg	0.002	N.D.	N.D.	N.D.	≤0.002
O-Anisidine	mg/kg	0.002	N.D.	N.D.	N.D.	≤0.002
Other Primary Aromatic Amines	mg/kg	0.01	N.D.	N.D.	N.D.	≤0.01
Comment(s)*	---	---	PASS			---

Remark:

*According to Regulation (EU) No 10/2011 and its amendment (EU) 2020/1245, for repeated use materials and articles:

1) The applicable overall migration test shall be carried out three times on a single sample. The overall migration in the second test shall be lower than in the first test, and the overall migration in the third test

Suzhou Yacoo Wonder Testing Technology Co.,Ltd.

Add.: 8/F, No.112, Xinqing Road, Industrial Park, Suzhou, Jiangsu, China.

Web.: www.yacoo-wondertesting.com

Customer Service: service@wondertesting.cn

Report Query: report@wondertesting.cn

TEST REPORT

Report No.: YW202607015201E

Date: Aug. 13, 2026

Page: 6 / 13

shall be lower than in the second test. Compliance with the overall migration limit shall be verified on the basis of the level of the overall migration found in the third test.

2) Specific migration test(s) shall be carried out three times on a single sample. Compliance shall than be verified on the basis of the level of the migration found in the third test and on the basis of the stability of the material or article from the first to the third migration test. The stability of the material shall be considered insufficient if migration is observed above the level of detection in any of the three migration tests, and increases from the first migration test to the third migration test. In case of insufficient stability, compliance of the material shall not be established even in case the specific migration limit is not exceeded in any of the three tests. Irrespective of the above rules, a material or article shall never be considered to comply with the Regulation if in the first test a substance that is prohibited from migrating or from being released in detectable quantities.

4. Bisphenol A (BPA) content-(EU) 2024/3190

Test Method: With reference to EPA 3550C:2007, analysis was performed by LC-MS-MS.

Test Item	CAS No.	Unit	MDL	Test Result(s)	Limit
				1#	
Bisphenol A (BPA)	80-05-7	µg/kg	1	N.D.	Prohibition

5. Extractable Heavy Metals

Test Method: With reference to Technical Guide on Metals and Alloys used in food contact materials and articles of the 2nd edition in 2024, analysis was performed by ICP-OES & ICP-MS

Sample No.:	3#						
Test condition:	40°C, 1hour with Citric acid (5 g/L)						
Extractable Elements	MDL (mg/kg)	Test Result (mg/kg)					
		1 st Result	2 nd Result	1 st + 2 nd Result	7*Limit	3 rd Result	Limit
Silver (Ag)	0.01	N.D.	N.D.	N.D.	0.56	N.D.	0.08
Aluminum (Al)	0.01	N.D.	N.D.	N.D.	35	N.D.	5
Chromium (Cr)	0.01	0.10	0.02	0.12	7	N.D.	1
Cobalt (Co)	0.01	N.D.	N.D.	N.D.	0.14	N.D.	0.02
Copper (Cu)	0.01	N.D.	N.D.	N.D.	28	N.D.	4
Iron (Fe)	0.01	0.20	N.D.	0.20	280	N.D.	40
Magnesium (Mg)	0.01	N.D.	N.D.	N.D.	---	N.D.	---
Manganese (Mn)	0.01	N.D.	N.D.	N.D.	3.85	N.D.	0.55
Molybdenum (Mo)	0.01	N.D.	N.D.	N.D.	0.84	N.D.	0.12
Nickel (Ni)	0.01	0.09	N.D.	0.09	0.98	N.D.	0.14
Tin (Sn)	0.01	N.D.	N.D.	N.D.	700	N.D.	100
Titanium (Ti)	0.01	N.D.	N.D.	N.D.	---	N.D.	---

Suzhou Yacoo Wonder Testing Technology Co.,Ltd.

Add.: 8/F, No.112, Xinqing Road, Industrial Park, Suzhou, Jiangsu, China.

Web.: www.yacoo-wondertesting.com

Customer Service: service@wondertesting.cn

Report Query: report@wondertesting.cn

TEST REPORT

Report No.: YW202607015201E

Date: Aug. 13, 2026

Page: 7 / 13

Sample No.:	3#						
Test condition:	40°C, 1hour with Citric acid (5 g/L)						
Extractable Elements	MDL (mg/kg)	Test Result (mg/kg)					
		1 st Result	2 nd Result	1 st + 2 nd Result	7*Limit	3 rd Result	Limit
Vanadium (V)	0.01	N.D.	N.D.	N.D.	0.07	N.D.	0.01
Zinc (Zn)	0.01	N.D.	N.D.	N.D.	35	N.D.	5
Arsenic (As)	0.001	N.D.	N.D.	N.D.	0.014	N.D.	0.002
Barium (Ba)	0.01	N.D.	N.D.	N.D.	8.4	N.D.	1.2
Beryllium (Be)	0.01	N.D.	N.D.	N.D.	0.07	N.D.	0.01
Cadmium (Cd)	0.001	N.D.	N.D.	N.D.	0.035	N.D.	0.005
Mercury (Hg)	0.001	N.D.	N.D.	N.D.	0.021	N.D.	0.003
Lithium (Li)	0.01	N.D.	N.D.	N.D.	0.336	N.D.	0.048
Lead (Pb)	0.001	N.D.	N.D.	N.D.	0.070	N.D.	0.010
Antimony (Sb)	0.01	N.D.	N.D.	N.D.	0.28	N.D.	0.04
Thallium (Tl)	0.001	N.D.	N.D.	N.D.	0.007	N.D.	0.001
Zirconium (Zr)	0.01	N.D.	N.D.	N.D.	14	N.D.	2

Sample No.:	4#						
Test condition:	40°C, 1hour with Citric acid (5 g/L)						
Extractable Elements	MDL (mg/kg)	Test Result (mg/kg)					
		1 st Result	2 nd Result	1 st + 2 nd Result	7*Limit	3 rd Result	Limit
Silver (Ag)	0.01	N.D.	N.D.	N.D.	0.56	N.D.	0.08
Aluminum (Al)	0.01	N.D.	N.D.	N.D.	35	N.D.	5
Chromium (Cr)	0.01	N.D.	N.D.	N.D.	7	N.D.	1
Cobalt (Co)	0.01	N.D.	N.D.	N.D.	0.14	N.D.	0.02
Copper (Cu)	0.01	N.D.	N.D.	N.D.	28	N.D.	4
Iron (Fe)	0.01	0.20	N.D.	0.20	280	N.D.	40
Magnesium (Mg)	0.01	N.D.	N.D.	N.D.	---	N.D.	---
Manganese (Mn)	0.01	N.D.	N.D.	N.D.	3.85	N.D.	0.55
Molybdenum (Mo)	0.01	N.D.	N.D.	N.D.	0.84	N.D.	0.12
Nickel (Ni)	0.01	N.D.	N.D.	N.D.	0.98	N.D.	0.14
Tin (Sn)	0.01	N.D.	N.D.	N.D.	700	N.D.	100
Titanium (Ti)	0.01	N.D.	N.D.	N.D.	---	N.D.	---
Vanadium (V)	0.01	N.D.	N.D.	N.D.	0.07	N.D.	0.01
Zinc (Zn)	0.01	N.D.	N.D.	N.D.	35	N.D.	5

Suzhou Yacoo Wonder Testing Technology Co.,Ltd.

Add.: 8/F, No.112, Xinqing Road, Industrial Park, Suzhou, Jiangsu, China.

Web.: www.yacoo-wondertesting.com

Customer Service: service@wondertesting.cn

Report Query: report@wondertesting.cn

TEST REPORT

Report No.: YW202607015201E

Date: Aug. 13, 2026

Page: 8 / 13

Sample No.:	4#						
Test condition:	40°C, 1hour with Citric acid (5 g/L)						
Extractable Elements	MDL (mg/kg)	Test Result (mg/kg)					
		1 st Result	2 nd Result	1 st + 2 nd Result	7*Limit	3 rd Result	Limit
Arsenic (As)	0.001	N.D.	N.D.	N.D.	0.014	N.D.	0.002
Barium (Ba)	0.01	N.D.	N.D.	N.D.	8.4	N.D.	1.2
Beryllium (Be)	0.01	N.D.	N.D.	N.D.	0.07	N.D.	0.01
Cadmium (Cd)	0.001	N.D.	N.D.	N.D.	0.035	N.D.	0.005
Mercury (Hg)	0.001	N.D.	N.D.	N.D.	0.021	N.D.	0.003
Lithium (Li)	0.01	N.D.	N.D.	N.D.	0.336	N.D.	0.048
Lead (Pb)	0.001	N.D.	N.D.	N.D.	0.070	N.D.	0.010
Antimony (Sb)	0.01	N.D.	N.D.	N.D.	0.28	N.D.	0.04
Thallium (Tl)	0.001	N.D.	N.D.	N.D.	0.007	N.D.	0.001
Zirconium (Zr)	0.01	N.D.	N.D.	N.D.	14	N.D.	2

Remark:

1. MDL = Method Detection Limit.
2. N.D.= Not detected, less than MDL.
3. The submitted sample/component is a repeated use article. The migration test was carried out three times on the same article. The sum of the results of the first and second tests should not exceed seven times the limit (Result 1st test + Result 2nd test < 7* limit) and the Result 3rd should not exceed the limit.

6. Lead (Pb) Content

Test Method: With reference to EPA 3052-1996 & EPA 6010D-2018, analysis was performed by ICP-OES.

Test Item	Unit	MDL	Test Result(s)		Limit
			1#	2#	
Lead (Pb)	mg/kg	10	N.D.	N.D.	500

Test Method: With reference to EPA 3050B-1996&EPA 6010D-2018, analysis was performed by ICP-OES.

Test Item	Unit	MDL	Test Result(s)			Limit
			3#	4#	5#	
Lead (Pb)	mg/kg	10	N.D.	N.D.	N.D.	500

Remark: The above limit value was quoted according to EC Regulation 1907/2006, REACH Annex XVII (entry 63).

7. Cadmium (Cd) Content

Test Method: With reference to EN 1122- 2001 Method B, analysis was performed by ICP-OES.

Suzhou Yacoo Wonder Testing Technology Co.,Ltd.

Add.: 8/F, No.112, Xinqing Road, Industrial Park, Suzhou, Jiangsu, China. Web.: www.yacoo-wondertesting.com

Customer Service: service@wondertesting.cn

Report Query: report@wondertesting.cn

TEST REPORT

Report No.: YW202607015201E

Date: Aug. 13, 2026

Page: 9 / 13

Test Item	Unit	MDL	Test Result(s)			Limit
			1#	2#	6#	
Cadmium (Cd)	mg/kg	10	N.D.	N.D.	N.D.	100

Remark: The above limit value was quoted according to EC Regulation 1907/2006, REACH Annex XVII (entry 23).

8. Phthalates Content

Test Method: With reference to EN 14372-2004, analysis was performed by GC-MS.

Test Items	Unit	MDL	Test Results		Limit
			1#	6#	
Dibutyl Phthalate (DBP)	%	0.005	N.D.	N.D.	---
Benzylbutyl Phthalate (BBP)		0.005	N.D.	N.D.	---
Di-(2-ethylhexyl)Phthalate (DEHP)		0.005	N.D.	N.D.	---
Di-isobutyl phthalate (DIBP)		0.005	N.D.	N.D.	---
Total (DBP+BBP+DEHP+DIBP)		---	< 0.020	< 0.020	≤0.1

Test Items	Unit	MDL	Test Results		Limit
			1#	6#	
Di-iso-nonylphthalate (DINP)	%	0.005	N.D.	N.D.	---
Di-n-octylphthalate (DNOP)		0.005	N.D.	N.D.	---
Di-iso-decylphthalate (DIDP)		0.005	N.D.	N.D.	---
Total (DINP+DNOP+DIDP)		---	< 0.015	< 0.015	≤0.1

Remark: The above limit value was quoted according to EC Regulation 1907/2006, REACH Annex XVII (entry 51&52).

***** To be continued *****

TEST REPORT

Report No.: YW202607015201E

Date: Aug. 13, 2026

Page: 10 / 13

9. PAHs Contents

Test Method: With reference to AfPS GS 2019:01 PAK, analysis was performed by GC-MS.

Test Items	CAS No.	MDL (mg/kg)	Test Results (mg/kg)	Limit (mg/kg)	
			1#	Category I	Category II
Benzo[a]pyrene	50-32-8	0.1	N.D.	1	0.5
Benzo[e]pyrene	192-97-2	0.1	N.D.	1	0.5
Benzo[a]anthracene	56-55-3	0.1	N.D.	1	0.5
Chrysene	218-01-9	0.1	N.D.	1	0.5
Benzo[b]fluoranthene	205-99-2	0.1	N.D.	1	0.5
Benzo[j]fluoranthene	205-82-3	0.1	N.D.	1	0.5
Benzo[k]fluoranthene	207-08-9	0.1	N.D.	1	0.5
Dibenzo[a,h]anthracene	53-70-3	0.1	N.D.	1	0.5

LIMITS FOR PAHs:

Parameter	Category I	Category II
PAHs	Such articles include amongst other: 1. Sport equipment such as bicycles, golf clubs, racquets 2. House-hold utensils, trolleys, walking frames 3. tools for domestic use 4. clothing, footwear, gloves and sportwear 5. watch-straps, wrist-bands, masks, head-bands	Toys, including activity toys, and childcare articles

Remark: The above limit value was quoted according to EC Regulation 1907/2006, REACH Annex XVII (entry 50).

10. Pentachlorophenol (PCP) Content

Test Method: With reference to EPA3550C-2007&EPA 8270E-2018, analysis was performed by GC-MS.

Test Item	Unit	MDL	Test Result(s)	Limit
			2#	
Pentachlorophenol (PCP)	mg/kg	0.05	N.D.	5

Remark: The above limited value was quoted according to Regulation (EU) 2019/1021 of the European Parliament and of the Council of 20 June 2019 on persistent organic pollutants (POPs) and its subsequent amendments regulation.

***** To be continued *****

Suzhou Yacoo Wonder Testing Technology Co.,Ltd.

Add.: 8/F, No.112, Xinqing Road, Industrial Park, Suzhou, Jiangsu, China.

Web.: www.yacoo-wondertesting.com

Customer Service: service@wondertesting.cn

Report Query: report@wondertesting.cn

TEST REPORT

Report No.: YW202607015201E

Date: Aug. 13, 2026

Page: 11 / 13

11. Formaldehyde release


Test method: With reference to EN 717-1:2004, analysis was performed by UV-Vis.

Test Parameter	Unit	MDL	Test Result(s)	Permissible Limit
			2#	
Formaldehyde	mg/m ³	0.040	N.D.	≤0.062

Remark: The above limit value was quoted according to EC Regulation 1907/2006, REACH Annex XVII (entry 77).

- Note: 1. MDL= Method Detection Limit
2. N.D. = Not Detected, <MDL

***** To be continued *****



TEST REPORT

Report No.: YW202607015201E


Date: Aug. 13, 2026

Page: 12 / 13


SAMPLE PHOTO(S)




1#




2#



3#



4#



5#



6#

TEST REPORT

Report No.: YW202607015201E

Date: Aug. 13, 2026

Page: 13 / 13

PRODUCT PHOTO(S)



Stainless steel hip flask (MO6356)

Statement:

1. This report is considered invalid without approved signature and special seal of the laboratory.
2. The sample(s) and sample(s) information was/were provided by the applicant who should be responsible for the authenticity.
3. The result(s) shown in this report refer(s) only to the sample(s) tested.
4. Without written approval of the laboratory, this report shall not be reproduced except in full. The report is invalid if altered.
5. Unless otherwise stated, the decision rule for conformity reporting is based on Binary Statement for Simple Acceptance Rule ($w=0$) stated in LAC-G8.09/2019. According to this rule, the judgement of conformity is based on the comparing test results with limits. The statement of conformity is based on the test results, but does not include the measurement uncertainty.
6. Without prior approval of YACOO WONDER, the client shall not use the testing data and results for improper publicity.
7. If there is any objection to the report, client shall lodge a complaint with the company on the 15 working days from the date of receipt of the report. No late application will be accepted.

***** END OF REPORT *****