TEST REPORT

Report No.	:	WTF26F05128318C
Job No.	:	FSW2605110375CJ
Applicant	:	Mid Ocean Brands B.V.
Address	:	Unit 711-716, 7/F., Tower A, 83 King Lam Street, Cheung Sha Wan, Kowloon, Hong Kong.
Manufacturer	:	105198
Sample Name	:	Wireless mouse in car shape
Sample Model	:	MO7641
Test Requested	:	With reference to Annex XVII Items 50 of REACH Regulation (EC) No.1907/2006 & the amendment Regulation (EU) No 1272/2013, to determine the Polycyclic Aromatic Hydrocarbons (PAHs) content in the submitted sample.
Test Method	:	Refer to next page (s)
Test Conclusion	:	**Pass**
Date of Receipt Sample	:	2026-05-11
Testing Period	:	2026-05-11 to 2026-05-20
Date of Issue	:	2026-05-20
Test Result	:	Refer to next page (s)

Prepared By:
Waltek Testing Group (Foshan) Co., Ltd.
Address: No.13-19, 2/F., 2nd Building, Sunlink Machinery City, Xingye 4 Road, Guanglong Industrial Park, Chihua Neighborhood Committee, Chencun, Shunde District, Foshan, Guangdong, China
Tel:+86-757-23811398 Fax:+86-757-23811381 E-mail:info@waltek.com.cn

Signed for and on behalf of
Waltek Testing Group (Foshan) Co., Ltd.

WTF26F05128318C

Swing Liang
Waltek Testing Group (Foshan) Co., Ltd.
http://www.waltek.com.cn

Sample photo:

MO7641

MO7641

Test Results:

Test Method/Equipment:

-With reference to AFPS GS 2019:01 PAK, determination of Polycyclic Aromatic Hydrocarbons (PAHs) by GC-MS

Test Item(s)	CAS No.	Unit	LOQ	Result(s)	Limit
				No.(1+3+4)#	
Benzo(a)anthracene (BaA)	56-55-3	mg/kg	0.2	ND	1.0
Chrysene (CHR)	218-01-9	mg/kg	0.2	ND	1.0
Benzo(b)fluoranthene (BbF)	205-99-2	mg/kg	0.2	ND	1.0
Benzo(k)fluoranthene (BkF)	207-08-9	mg/kg	0.2	ND	1.0
Benzo(a)pyrene (BaP)	50-32-8	mg/kg	0.2	ND	1.0
Dibenzo(a,h)anthracene (DBA)	53-70-3	mg/kg	0.2	ND	1.0
Benzo(j)fluoranthene	205-82-3	mg/kg	0.2	ND	1.0
Benzo(e)Pyrene	192-97-2	mg/kg	0.2	ND	1.0
Conclusion	--	--	--	**Pass**	--

Test Item(s)	CAS No.	Unit	LOQ	Result(s)	Limit
				No.(5+7+8)#	
Benzo(a)anthracene (BaA)	56-55-3	mg/kg	0.2	ND	1.0
Chrysene (CHR)	218-01-9	mg/kg	0.2	ND	1.0
Benzo(b)fluoranthene (BbF)	205-99-2	mg/kg	0.2	ND	1.0
Benzo(k)fluoranthene (BkF)	207-08-9	mg/kg	0.2	ND	1.0
Benzo(a)pyrene (BaP)	50-32-8	mg/kg	0.2	ND	1.0
Dibenzo(a,h)anthracene (DBA)	53-70-3	mg/kg	0.2	ND	1.0
Benzo(j)fluoranthene	205-82-3	mg/kg	0.2	ND	1.0
Benzo(e)Pyrene	192-97-2	mg/kg	0.2	ND	1.0
Conclusion	--	--	--	**Pass**	--

Test Item(s)	CAS No.	Unit	LOQ	Result(s)	Limit
				No.6	
Benzo(a)anthracene (BaA)	56-55-3	mg/kg	0.2	ND	1.0
Chrysene (CHR)	218-01-9	mg/kg	0.2	ND	1.0
Benzo(b)fluoranthene (BbF)	205-99-2	mg/kg	0.2	ND	1.0
Benzo(k)fluoranthene (BkF)	207-08-9	mg/kg	0.2	ND	1.0
Benzo(a)pyrene (BaP)	50-32-8	mg/kg	0.2	ND	1.0
Dibenzo(a,h)anthracene (DBA)	53-70-3	mg/kg	0.2	ND	1.0
Benzo(j)fluoranthene	205-82-3	mg/kg	0.2	ND	1.0
Benzo(e)Pyrene	192-97-2	mg/kg	0.2	ND	1.0
Conclusion	--	--	--	**Pass**	--

Test Item(s)	CAS No.	Unit	LOQ	Result(s)	Limit
				No.(9+16 +19)#	
Benzo(a)anthracene (BaA)	56-55-3	mg/kg	0.2	ND	1.0
Chrysene (CHR)	218-01-9	mg/kg	0.2	ND	1.0
Benzo(b)fluoranthene (BbF)	205-99-2	mg/kg	0.2	ND	1.0
Benzo(k)fluoranthene (BkF)	207-08-9	mg/kg	0.2	ND	1.0
Benzo(a)pyrene (BaP)	50-32-8	mg/kg	0.2	ND	1.0
Dibenzo(a,h)anthracene (DBA)	53-70-3	mg/kg	0.2	ND	1.0
Benzo(j)fluoranthene	205-82-3	mg/kg	0.2	ND	1.0
Benzo(e)Pyrene	192-97-2	mg/kg	0.2	ND	1.0
Conclusion	--	--	--	**Pass**	--

Note:

(1)mg/kg (milligram per kilogram) = ppm (parts per million)

(2)ND=Not Detected or lower than limit of quantitation

(3)LOQ =Limit of quantitation

(4)"--"=Not regulated

(5)#=As per applicant's requirement, the testing was conducted based on mixed components by weight in equal ratio, results are calculated by the minimum weight of mixed components.

(6)As per Annex XVII Items 50 of REACH Regulation (EC) No.1907/2006 & the amendment Regulation (EU) No 1272/2013, Articles shall not be placed on the market for supply to the general public, if any of their rubber or plastic components that come into direct as well as prolonged or short-term repetitive contact with the human skin or the oral cavity, under normal or reasonably foreseeable conditions of use, contain more than 1 mg/kg (0.0001 % by weight of this component) of any of the listed PAHs.

(7)As per Annex XVII Items 50 of REACH Regulation (EC) No.1907/2006 & the amendment Regulation (EU) No 1272/2013, Toys, including activity toys, and childcare articles, shall not be placed on the market, if any of their rubber or plastic components that come into direct as well as prolonged or short-term repetitive contact with the human skin or the oral cavity, under normal or reasonably foreseeable conditions of use, contain more than 0.5 mg/kg (0.00005 % by weight of this component) of any of the listed PAHs.

Testing Flow chart:



Description for Specimen:

Specimen ID	Specimen No.	Specimen Description
FSW2605110375CJ. 1	1	Black soft plastic ring
FSW2605110375CJ. 3	3	Black plastic shell
FSW2605110375CJ. 4	4	Transparent plastic sheet
FSW2605110375CJ. 5	5	Red transparent plastic sheet
FSW2605110375CJ. 6	6	Silvery coating
FSW2605110375CJ. 7	7	Black plastic shell without silvery coating
FSW2605110375CJ. 8	8	Black plastic cap with silvery plating
FSW2605110375CJ. 9	9	Black plastic wheel
FSW2605110375CJ. 16	16	Black plastic shell
FSW2605110375CJ. 19	19	Semi-transparent plastic shell

Photograph of parts tested:

<table>
<tr>
<td> 
</td>
<td> 
</td>
</tr>
<tr>
<td>
</td>
<td>/</td>
</tr>
</table>

Remarks:

1. The results shown in this test report refer only to the sample(s) tested;
2. This test report cannot be reproduced, except in full, without prior written permission of the company;
3. The report would be invalid without specific stamp of test institute and the signatures of compiler and approver;
4. The Applicant name and Address, the sample(s) and sample information was/were provided by the applicant who should be responsible for the authenticity which Waltek hasn't verified;
5. If the report is not stamped with the accreditation recognized seal, it will only be used for scientific research, education, and internal quality control activities, and is not used for the purpose of issuing supporting data to the society.
6. The sample material information (Model No. information) is provided by client, not verified by test laboratory. The samples of reference Model No. are not tested. Test laboratory not responsible for the accuracy, appropriateness, completeness and authenticity of the information provided by client.

====== End of Report ======