



TEST REPORT

Report No.: JTS25110355-2ER1

Date: Dec. 03, 2025

Page 1 of 24

Client: Mid Ocean Brands B.V.

Address: Unit 711 - 716, 7/F., Tower A, 83 King Lam Street, Cheung Sha Wan, Kowloon, Hong Kong

The following merchandise was (were) submitted and identified by the client as:

Name of Product: Chess board wine set Wine set in bamboo box

Model No.: MO2393 MO8293

Supplier: 103225

Sample Received: Nov. 03, 2025

Test Period: Nov. 03, 2025 - Nov. 18, 2025

Nov. 28, 2025 - Dec. 03, 2025

This report replaces the original report which is numbered JTS25110355-2E.

Overall Result : PASS

Test specification : Please refer to next page.

Prepared by : *Luna Zhao*

Luna Zhao

Report editor

Reviewed By : *Sigrid Shentu*

Sigrid Shentu

Quality Manager

Issued By : *Carl Zhu*

Carl Zhu

Authorized Signatory



NPS Survey



Verification Report

Zhejiang J-testing Service Co., Ltd.

Add: West of 3/F, No.5 Building, No.968 Xuefeng West Road, Beiyuan Street, Yiwu, Zhejiang, China 322000
Customer service: info@j-testing.com/+86 057985309611 Web: www.jts-cert.com

TEST REPORT

Report No.: JTS25110355-2ER1

Date: Dec. 03, 2025

Page 2 of 24

Test Requested and Conclusion(s):

No.	Test Requested	Conclusion(s)
1	German Food, Articles of Daily Use and Feed Code of September 1, 2005 (LFGB), Section 30, and Technical Guide on Council of Europe Resolution CM/Res(2020)9, Technical Guide on Metals and Alloys used in food contact materials and articles of the 2 nd edition in 2024, General Requirement (Article 3) in EU Regulation (EC) No 1935/2004	
1-1	-Extractable Heavy Metals for Metal	PASS
2	Entry 77 of Regulation (EU) 2023/1464 amending Annex XVII of REACH Regulation (EC) No 1907/2006 -Formaldehyde Release	PASS
3	German Food, Articles of Daily Use and Feed Code of September 1, 2005 (LFGB), Section 30 and BfR recommendation. General Requirement (Article 3) in EU Regulation No. 1935/2004	
3-1	-Overall Migration test for silicone rubber	PASS
3-2	-Peroxide value for Silicone rubber	PASS
3-3	-Volatile organic matter (VOM) for Silicone rubber	PASS
3-4	-Specific migration of organotin (as Tin) for Silicone rubber	PASS
3-5	-Bisphenol-A (BPA) content for Silicone rubber	PASS
4	1907/2006 REACH Annex XVII Item 63 - Total Lead (Pb)	PASS
5	1907/2006 REACH Annex XVII Item 23 - Total Cadmium (Cd)	PASS
6	Regulation (EU) 2019/1021 of the European Parliament and of the Council of 20 June 2019 on persistent organic pollutants and its subsequent amendments Directive. - Pentachlorophenol (PCP) content	PASS
7	BS EN 12875-1:2005 Mechanical dishwashing resistance of utensils - Part 1: Reference test method for domestic articles	PASS
8	1907/2006 REACH Annex XVII Item 51&52 - Phthalates	PASS
9	1907/2006 REACH Annex XVII Item 43 - AZO	PASS
10	1907/2006 REACH Annex XVII Item 50 - Polycyclic Aromatic Hydrocarbons (PAHs) content	PASS
11	1907/2006 REACH Annex XVII Item 5 - Benzene	PASS
12	-Colour fastness to rubbing - Client's limit	PASS

*** To be continued ***

Test Result(s):

1-1.Extractable Heavy Metals

Method: with reference to Technical Guide on Metals and Alloys used in food contact materials and articles of the 2nd edition in 2024 and by Inductively Coupled Plasma Mass Spectrometry (ICP-MS).

Material No.	15					
Extractable Elements	The 1 st Result(mg/kg)	The 2 nd Result (mg/kg)	The 1 st + 2 nd Result (mg/kg)	7*Limit (mg/kg)	The 3 rd Result(mg/kg)	Limit (mg/kg)
Silver(Ag)	N.D.	N.D.	N.D.	0.56	N.D.	0.08
Aluminium (Al)	N.D.	N.D.	N.D.	35	N.D.	5
Chromium(Cr)	N.D.	N.D.	N.D.	7	N.D.	1
Cobalt (Co)	N.D.	N.D.	N.D.	0.14	N.D.	0.02
Copper(Cu)	N.D.	N.D.	N.D.	28	N.D.	4
Iron(Fe)	N.D.	N.D.	N.D.	280	N.D.	40
Magnesium (Mg)	N.D.	N.D.	N.D.	--	N.D.	--
Manganese (Mn)	N.D.	N.D.	N.D.	3.85	N.D.	0.55
Molybdenum(Mo)	N.D.	N.D.	N.D.	0.84	N.D.	0.12
Nickel (Ni)	N.D.	N.D.	N.D.	0.98	N.D.	0.14
Tin (Sn)	N.D.	N.D.	N.D.	700	N.D.	100
Titanium(Ti)	N.D.	N.D.	N.D.	--	N.D.	--
Vanadium(V)	N.D.	N.D.	N.D.	0.07	N.D.	0.01
Zinc(Zn)	N.D.	N.D.	N.D.	35	N.D.	5
Antimony(Sb)	N.D.	N.D.	N.D.	0.28	N.D.	0.04
Arsenic (As)	N.D.	N.D.	N.D.	0.014	N.D.	0.002
Barium(Ba)	N.D.	N.D.	N.D.	8.4	N.D.	1.2
Beryllium (Be)	N.D.	N.D.	N.D.	0.07	N.D.	0.01
Cadmium(Cd)	N.D.	N.D.	N.D.	0.035	N.D.	0.005
Lead(Pb)	N.D.	N.D.	N.D.	0.07	N.D.	0.01
Lithium (Li)	N.D.	N.D.	N.D.	0.336	N.D.	0.048
Mercury (Hg)	N.D.	N.D.	N.D.	0.021	N.D.	0.003
Thallium (Tl)	N.D.	N.D.	N.D.	0.007	N.D.	0.001
Zirconium (Zr)	N.D.	N.D.	N.D.	14	N.D.	2
Conclusion	PASS					

- Note:**
1. mg/kg = milligram per kilogram (ppm).
 2. MDL= Method detection limit.
 3. N.D. = Not detected, less than MDL.
 4. Test condition: 70 °C, 2 hours with Citric Acid.
 5. The submitted sample/component is a repeated use article. The migration test was carried out three times on the same article. The sum of the results of the first and second tests should not exceed seven times the limit (Result 1st test + Result 2nd test < 7* limit) and the Result 3rd should not exceed the limit.

Remark:

1. The following table is the MDL of the Extractable Heavy Metals testing

Extractable Elements	MDL(mg/kg)	Extractable Elements	MDL(mg/kg)	Extractable Elements	MDL(mg/kg)
Silver (Ag)	0.001	Molybdenum (Mo)	0.001	Barium (Ba)	0.1
Aluminium (Al)	0.1	Nickel (Ni)	0.05	Beryllium (Be)	0.001
Chromium (Cr)	0.05	Tin (Sn)	0.1	Cadmium (Cd)	0.0001
Cobalt (Co)	0.001	Titanium (Ti)	0.1	Lead (Pb)	0.001
Copper (Cu)	0.1	Vanadium (V)	0.001	Lithium (Li)	0.001
Iron (Fe)	0.1	Zinc (Zn)	0.1	Mercury (Hg)	0.0001
Magnesium (Mg)	0.1	Antimony (Sb)	0.001	Thallium (Tl)	0.0001
Manganese (Mn)	0.1	Arsenic (As)	0.0001	Zirconium (Zr)	0.001

*** To be continued ***

TEST REPORT

Report No.: JTS25110355-2ER1

Date: Dec. 03, 2025

Page 5 of 24

2.Entry 77 of Regulation(EU)2023/1464 amending Annex XVII of REACH Regulation(EC)No 1907/2006- Formaldehyde Release

Method:With reference to EN717-1:2004 and Regulation (EU)2023/1464 Appendix 14,paragraph
1,analysis was performed by UV-Vis.

Test Item(s)	Limit	Unit(s)	MDL	4
Test chamber parameters				
Chamber Volume	-	m ³	-	1.00
Testing climate-Temperature	-	°C	-	23.0
Testing climate-Relative Humidity	-	%	-	45
Ventilation (Air Change Rate)	-	/h	-	1.0
Sample Loading factor	-	m ² /m ³	-	1.000
Sampling Flow Rate	-	L/min	-	2.0
Sampling Time	-	min	-	60
Sampling Volume	-	L	-	120
Test result				
Formaldehyde Release(In air)	0.062	mg/m ³	0.050	ND
Conclusion				PASS

Test Item(s)	Limit	Unit(s)	MDL	5
Test chamber parameters				
Chamber Volume	-	m ³	-	1.00
Testing climate-Temperature	-	°C	-	23.0
Testing climate-Relative Humidity	-	%	-	45
Ventilation (Air Change Rate)	-	/h	-	1.0
Sample Loading factor	-	m ² /m ³	-	1.000
Sampling Flow Rate	-	L/min	-	2.0
Sampling Time	-	min	-	60
Sampling Volume	-	L	-	120
Test result				
Formaldehyde Release(In air)	0.062	mg/m ³	0.050	ND
Conclusion				PASS

The data of point 4 is derived from the report numbered point 2 of JTS25090259-1ER2.

*** To be continued ***

Notes:

(1) At 23°C and 1013 hPa, the following relationship exists for formaldehyde:

1 ppm (parts per million) = 1.24 mg/m³

1 mg/m³ = 0.81 ppm (parts per million)

(2) Reference Limit:

Regulation (EU) 2023/1464 of July 14, 2023, amending Annex XVII of REACH as regards formaldehyde and formaldehyde releasers, Official Journal of the EU, July 17, 2023

Scope	Requirement	Method	Effective Date
Furniture and wood-based articles	≤0.062 mg/m ³	Chamber method as described in Appendix 14, paragraph 1	After August 6, 2026
Articles other than furniture and wood-based articles	≤0.080 mg/m ³		
Interior of road vehicles, including trucks and buses	≤0.062 mg/m ³	Ambient mode according to ISO 12219-1 or ISO 12219-10 (see Appendix 14, paragraph 2)	After August 6, 2027

Unless otherwise stated, the decision rule for conformity reporting is based on Binary Statement for Simple Acceptance Rule (w=0) stated in ILAC-G8:09/2019.

*** To be continued ***

3-1. Overall migration

Method: With reference to EN 1186-1:2002 for selection of conditions and test methods;

EN 1186-3:2022 for overall migration in evaporable simulants;

Surface area(dm²)/Volume(ml): 1/100

Simulants	Unit	Test Condition	Result			Maximum Permissible Limit	Conclusion
			16 ^{-1st}	16 ^{-2nd}	16 ^{-3rd}		
3% acetic acid	mg/dm ²	2 hours at 70°C	<3	<3	<3	10	PASS
50% ethanol	mg/dm ²	2 hours at 70°C	4	<3	<3	10	PASS

The data of point 16 is derived from the report numbered point 10 of JTS25090259-1ER2.

3-2. Peroxide Value

Method: With reference to European pharmacopoeia, 2005 Appendix X F. Peroxide Value method A

Test Items	Result	Maximum Permissible Limit
	16	
Peroxide Value	Absent	Absent

The data of point 16 is derived from the report numbered point 10 of JTS25090259-1ER2.

3-3. Volatile Organic Matter

Method: With reference to Determination of volatile compounds in silicone consumer products

Test condition: 200 °C, 4 hours

Test Item	Unit	Result	Maximum Permissible Limit	Conclusion
		16		
Volatile organic matter (VOM)	%	<0.1	0.5	PASS

The data of point 16 is derived from the report numbered point 10 of JTS25090259-1ER2.

*** To be continued ***

3-4. Specific Migration of Tin

Method: Sample preparation in 3% acetic acid at 70 °C for 2 hours, followed by analysis using Inductively Coupled Argon Plasma Spectrometry.

Test Items	Unit	Result			Maximum Permissible Limit
		16 ^{-1st}	16 ^{-2nd}	16 ^{-3rd}	
Specific migration of Tin in 3% acetic acid	mg/kg	<0.01	<0.01	<0.01	0.1
Conclusion	---	PASS			---

The data of point 16 is derived from the report numbered point 10 of JTS25090259-1ER2.

3-5. Bisphenol-A (BPA) Content

Method: With reference to EPA3550C-2007, Analysis was performed by UPLC-MS-MS.

Test Item	Unit	MDL	Test Results	Limit
			16	
Bisphenol-A (BPA)	mg/kg	0.1	N.D.	Absent

The data of point 16 is derived from the report numbered point 10 of JTS25090259-1ER2.

*** To be continued ***

4.Total Lead (Pb)

Method: With reference to CPSC-CH-E1001-08.3, analyzed by Atomic Absorption Spectroscopy (AAS)

Material No.	Limit (mg/kg)	Result (mg/kg)	Conclusion
6+7+8*	500	32	PASS
10+11+12*	500	26	PASS
13+14+15*	500	140	PASS
19	500	20	PASS
21+22+23*	500	20	PASS
24+25+26*	500	24	PASS
28+29+30*	500	22	PASS

4.Total Lead (Pb)

Method: With reference to CPSC-CH-E1002-08.3, analyzed by Atomic Absorption Spectroscopy (AAS)

Material No.	Limit (mg/kg)	Result (mg/kg)	Conclusion
4	500	N.D.	PASS
5	500	N.D.	PASS
9	500	14	PASS
16	500	N.D.	PASS
17	500	N.D.	PASS
18	500	N.D.	PASS
20	500	N.D.	PASS
31	500	N.D.	PASS

*** To be continued ***

TEST REPORT

Report No.: JTS25110355-2ER1

Date: Dec. 03, 2025

Page 10 of 24

4.Total Lead (Pb)

Method: With reference to CPSC-CH-E1003-09.1, analyzed by Atomic Absorption Spectroscopy (AAS)

Material No.	Limit (mg/kg)	Result (mg/kg)	Conclusion
1+2+3*	500	N.D.	PASS

- Note:**
1. mg/kg = milligram per kilogram (ppm).
 2. MDL (Method detection limit) = 10 mg/kg.
 3. N.D. = Not detected, less than MDL.
 4. "*" According to the customer's requirements, the samples were mixed tested. The test result is the overall result of mixed samples. And may be different from any single test result.
 5. The data of point 4,16 is derived from the report numbered point 2,10 of JTS25090259-1ER2.

5.Total Cadmium (Cd)

Method: With reference to CPSC-CH-E1001-08.3, analyzed by Atomic Absorption Spectroscopy (AAS)

Material No.	Limit (mg/kg)	Result (mg/kg)	Conclusion
6+7+8*	100	N.D.	PASS
10+11+12*	100	N.D.	PASS
13+14+15*	100	N.D.	PASS
19	100	N.D.	PASS
21+22+23*	100	N.D.	PASS
24+25+26*	100	N.D.	PASS
28+29+30*	100	N.D.	PASS

5.Total Cadmium (Cd)

Method: With reference to CPSC-CH-E1002-08.3, analyzed by Atomic Absorption Spectroscopy (AAS)

Material No.	Limit (mg/kg)	Result (mg/kg)	Conclusion
9	100	N.D.	PASS
16	100	N.D.	PASS
17	100	N.D.	PASS
18	100	N.D.	PASS
20	100	N.D.	PASS
31	100	N.D.	PASS

*** To be continued ***

5. Total Cadmium (Cd)

Method: With reference to CPSC-CH-E1003-09.1, analyzed by Atomic Absorption Spectroscopy (AAS)

Material No.	Limit (mg/kg)	Result (mg/kg)	Conclusion
1+2+3*	1000	N.D.	PASS

- Note:**
1. mg/kg = milligram per kilogram (ppm).
 2. MDL (Method detection limit) = 10 mg/kg.
 3. N.D. = Not detected, less than MDL.
 4. "*" According to the customer's requirements, the samples were mixed tested. The test result is the overall result of mixed samples. And may be different from any single test result.
 5. The data of point 16 is derived from the report numbered point 10 of JTS25090259-1ER2.

6. Pentachlorophenol (PCP) Content

Method: Analysis was performed by Gas Chromatograph-Mass Spectrometry (GC-MS).

Test Item	MDL(mg/kg)	Test Results(mg/kg)	Limited Value(mg/kg)	Conclusion
		4		
Pentachlorophenol (PCP)	0.1	N.D.	5	PASS

Test Item	MDL(mg/kg)	Test Results(mg/kg)	Limited Value(mg/kg)	Conclusion
		5		
Pentachlorophenol (PCP)	0.1	N.D.	5	PASS

- Note:**
1. mg/kg = milligram per kilogram (ppm).
 2. MDL = Method detection limit.
 3. N.D. = Not detected, less than MDL.
 4. The data of point 4 is derived from the report numbered point 2 of JTS25090259-1ER2.

*** To be continued ***

7.BS EN 12875-1:2005 Mechanical dishwashing resistance of utensils - Part 1: Reference test method for domestic articles (Whole Product)

Method: BS EN 12875-1:2005 Mechanical dishwashing resistance of utensils — Part 1: Reference test method for domestic articles

1. Visually inspect samples and record any cosmetic defects
2. Load the dishwasher with tested samples. The other sample will be used as the standard.
3. Fill the dishwasher soap holder with the powder detergent, close and lock the dishwasher as recommended in the operating instructions.
4. Run the dishwasher for 10 cycles with 149°F(65°C) water at “normal setting” for housewares. Each cycle includes soaking, washing and drying
5. Remove and visually examine each sample

Test Requirement: The sample shall show no signs of discoloration or cracking after testing.

Sample size: 1 pieces

Test result: details show as following table:

Washing Cycle Sample No.	1 st	2 nd	3 rd	4 th	5 th	6 th	7 th	8 th	9 th	10 th
13	P	P	P	P	P	P	P	P	P	P
27	P	P	P	P	P	P	P	P	P	P

The data of point 13 is derived from the report numbered point 9 of JTS25090259-1ER2.

*** To be continued ***

8. Phthalates

Method: With reference to EN ISO 14389:2022, analyzed by Gas Chromatograph-Mass Spectrometer (GC-MS).

Substances	CAS No.	MDL(%)	Limit (%)	Result (%)		
				1+2+3*	9	16
DIBP	84-69-5	0.005	--	N.D.	N.D.	N.D.
DBP	84-74-2	0.005	--	N.D.	N.D.	N.D.
DEHP	117-81-7	0.005	--	N.D.	N.D.	N.D.
BBP	85-68-7	0.005	--	N.D.	N.D.	N.D.
SUM	--	--	<0.1	<0.1	<0.1	<0.1
DNOP	117-84-0	0.005	--	N.D.	N.D.	N.D.
DINP	28553-12-0 /68515-48-0	0.010	--	N.D.	N.D.	N.D.
DIDP	26761-40-0 /68515-49-1	0.010	--	N.D.	N.D.	N.D.
SUM	--	--	<0.1	<0.1	<0.1	<0.1
Conclusion				PASS	PASS	PASS

Substances	CAS No.	MDL(%)	Limit (%)	Result (%)		
				18	20	31
DIBP	84-69-5	0.005	--	N.D.	N.D.	N.D.
DBP	84-74-2	0.005	--	N.D.	N.D.	N.D.
DEHP	117-81-7	0.005	--	N.D.	N.D.	N.D.
BBP	85-68-7	0.005	--	N.D.	N.D.	N.D.
SUM	--	--	<0.1	<0.1	<0.1	<0.1
DNOP	117-84-0	0.005	--	N.D.	N.D.	N.D.
DINP	28553-12-0 /68515-48-0	0.010	--	N.D.	N.D.	N.D.
DIDP	26761-40-0 /68515-49-1	0.010	--	N.D.	N.D.	N.D.
SUM	--	--	<0.1	<0.1	<0.1	<0.1
Conclusion				PASS	PASS	PASS

- Note:**
- MDL = Method detection limit.
 - N.D. = Not detected, less than MDL.
 - "*" According to the customer's requirements, the samples were mixed tested. The test result is the overall result of mixed samples. And may be different from any single test result.
 - The data of point 16 is derived from the report numbered point 10 of JTS25090259-1ER2.

TEST REPORT

Report No.: JTS25110355-2ER1

Date: Dec. 03, 2025

Page 14 of 24

9.AZO Contents

Method: With reference to EN ISO 14362-1:2017, analyzed by Gas Chromatograph-Mass Spectrometry (GC-MS).

No.	Substances Name	CAS No.	Limit (mg/kg)	Result (mg/kg)	
				17	20
1	biphenyl-4-ylamine/ 4-aminodiphenyl/ xenylamine	92-67-1	30	N.D.	N.D.
2	benzidine	92-87-5	30	N.D.	N.D.
3	4-chloro-o-toluidine	95-69-2	30	N.D.	N.D.
4	2-naphthylamine	91-59-8	30	N.D.	N.D.
5	o-aminoazotoluene/ 4-o-tolylazo-o-toluidine/ 4-amino-2', 3-dimethylazobenzene	97-56-3	30	N.D.	N.D.
6	2-amino-4-nitrotoluene/ 5-nitro-o-toluidine	99-55-8	30	N.D.	N.D.
7	4-chloroaniline	106-47-8	30	N.D.	N.D.
8	4-methoxy-m-phenylenediamine	615-05-4	30	N.D.	N.D.
9	4,4'-methylenedianiline/ 4,4'- diaminodiphenylmethane	101-77-9	30	N.D.	N.D.
10	3,3'-dichlorobenzidine/ 3,3'-dichlorobiphenyl-4,4'- ylenediamine	91-94-1	30	N.D.	N.D.
11	3,3'-dimethoxybenzidine/ o-dianisidine	119-90-4	30	N.D.	N.D.
12	3,3'-dimethylbenzidine/ 4,4'-bi-o-toluidine	119-93-7	30	N.D.	N.D.
13	4,4'-methylenedi-o-toluidine	838-88-0	30	N.D.	N.D.
14	6-methoxy-m-toluidine/ p-cresidine	120-71-8	30	N.D.	N.D.
15	4,4'-methylene-bis-(2-chloroaniline)/ 2,2'-dichloro- 4,4'-methylene-dianiline	101-14-4	30	N.D.	N.D.
16	4,4'-oxydianiline	101-80-4	30	N.D.	N.D.
17	4,4'-thiodianiline	139-65-1	30	N.D.	N.D.
18	o-toluidine/ 2-aminotoluene	95-53-4	30	N.D.	N.D.
19	4-methyl-m-phenylenediamine/ 2,4-toluylendiamine	95-80-7	30	N.D.	N.D.
20	2,4,5-trimethylaniline	137-17-7	30	N.D.	N.D.
21	o-anisidine / 2-methoxyaniline	90-04-0	30	N.D.	N.D.
22	4-aminoazobenzene	60-09-3	30	N.D.	N.D.
Conclusion				PASS	PASS

- Note:**
1. mg/kg = milligram per kilogram (ppm).
 2. MDL (Method detection limit) = 5mg/kg.
 3. N.D. = Not detected, less than MDL.

To be continued

Zhejiang J-testing Service Co.,Ltd.

Add: West of 3/F, No.5 Building, No.968 Xuefeng West Road, Beiyuan Street, Yiwu, ZheJiang, China 322000
Customer service: info@j-testing.com/+86 057985309611 Web: www.jts-cert.com

10. Polycyclic Aromatic Hydrocarbons (PAHs)

Method: With reference to AfPS GS 2019:01 PAK, analyzed by Gas Chromatograph-Mass Spectrometry (GC-MS).

Test Substance	CAS No.	Limit (mg/kg)	Result (mg/kg)		
		II	1+2+3*	9	16
Benzo[a]anthracene(BaA)	56-55-3	1	N.D.	N.D.	N.D.
Chrysene (CHR)	218-01-9	1	N.D.	N.D.	N.D.
Benzo[b]fluoranthene(BbF)	205-99-2	1	N.D.	N.D.	N.D.
Benzo[k]fluoranthene(BkF)	207-08-9	1	N.D.	N.D.	N.D.
Benzo[a]pyrene(BaP)	50-32-8	1	N.D.	N.D.	N.D.
Dibenzo[a,h]anthracene(DBA)	53-70-3	1	N.D.	N.D.	N.D.
Benzo[e]pyrene(BeP)	192-97-2	1	N.D.	N.D.	N.D.
Benzo[j]fluoranthene(BjF)	205-82-3	1	N.D.	N.D.	N.D.
SUM		--	--	--	--
Conclusion			PASS	PASS	PASS

Test Substance	CAS No.	Limit (mg/kg)	Result (mg/kg)		
		II	18	20	31
Benzo[a]anthracene(BaA)	56-55-3	1	N.D.	N.D.	N.D.
Chrysene (CHR)	218-01-9	1	N.D.	N.D.	N.D.
Benzo[b]fluoranthene(BbF)	205-99-2	1	N.D.	N.D.	N.D.
Benzo[k]fluoranthene(BkF)	207-08-9	1	N.D.	N.D.	N.D.
Benzo[a]pyrene(BaP)	50-32-8	1	N.D.	N.D.	N.D.
Dibenzo[a,h]anthracene(DBA)	53-70-3	1	N.D.	N.D.	N.D.
Benzo[e]pyrene(BeP)	192-97-2	1	N.D.	N.D.	N.D.
Benzo[j]fluoranthene(BjF)	205-82-3	1	N.D.	N.D.	N.D.
SUM		--	--	--	--
Conclusion			PASS	PASS	PASS

To be continued

- Note:**
1. mg/kg = milligram per kilogram (ppm).
 2. MDL (Method detection limit) = 0.20 mg/kg.
 3. N.D. = Not detected, less than MDL.
 4. "--" = Not Regulated.
 5. Product Class:
 I = Extender oils.
 II = Rubber or plastic components that come into direct as well as prolonged or short-term repetitive contact with the human skin or the oral cavity, under normal or reasonably foreseeable conditions of use.
 III = Toys, including activity toys, and childcare articles, if any of their rubber or plastic components that come into direct as well as prolonged or short-term repetitive contact with the human skin or the oral cavity, under normal or reasonably foreseeable conditions of use.
 6. "*" According to the customer's requirements, the samples were mixed tested. The test result is the overall result of mixed samples. And may be different from any single test result.
 7. The data of point 16 is derived from the report numbered point 10 of JTS25090259-1ER2.

11. Benzene Content

Method: With reference to EPA 8260C-2006, Analysis was performed by HS-GC-FID.

Material No.	Limit (mg/kg)	Result (mg/kg)	Conclusion
1+2+3*	1000	N.D.	PASS
9	1000	N.D.	PASS
16	1000	N.D.	PASS
17	1000	N.D.	PASS
18	1000	N.D.	PASS
20	1000	N.D.	PASS
31	1000	N.D.	PASS

- Note:**
1. mg/kg = milligram per kilogram (ppm).
 2. MDL (Method detection limit) = 50 mg/kg.
 3. N.D. = Not detected, less than MDL.
 4. "*" According to the customer's requirements, the samples were mixed tested. The test result is the overall result of mixed samples. And may be different from any single test result.

To be continued

12. Colour fastness to rubbing (Unit: Grade)

Method: ISO 105-X12

Sample	Requirement	Result		Conclusion
17	Dry $\geq 2-3$	Dry	4-5	PASS
	Wet $\geq 2-3$	Wet	4	

Sample	Requirement	Result		Conclusion
20	Dry $\geq 2-3$	Dry	3	PASS
	Wet $\geq 2-3$	Wet	2-3	

Note:

Explanation of colorfastness results:

- Grade 5 negligible or no changing or staining
- Grade 4 slightly changing or staining
- Grade 3 noticeably changing or staining
- Grade 2 considerably changing or staining
- Grade 1 much changing or heavily staining

To be continued

TEST REPORT

Report No.: JTS25110355-2ER1

Date: Dec. 03, 2025

Page 18 of 24

Test Material List:


Material No.	Description	Location
1	Transparent varnish	Coating of chess pieces(Chess piece)
2	Brown coating	Coating of brown chess pieces
3	Transparent varnish	Coating of bamboo box
4	Light brown bamboo	Bamboo box
5	White wood	Substrate of chess pieces
6	Silver metal	Latch base
7	Silver metal	Screw
8	Silver metal	Rivet
9	Black foam	Inner liner
10	Silver metal	Bottle opener
11	Silver metal	Bottle opener spiral
12	Silver metal	Knife
13	Silver metal	Bottle stopper with metal handle
14	Silver metal	Wine collar
15	Silver metal	Bottle stopper with bamboo handle(MO8293)
16	Black silicone	Silicone ring (Bottle stopper)
17	Black fabric	Metal ring inner ring
18	Black plastic	Plastic foil cutter
19	Golden metal	Rivet A(MO8293)
20	Black fabric with transparent glue	Inner lining surface(MO8293)
21	Silver metal	Plectrum
22	Silver metal	Connect slice
23	Silver metal	Elastic metal sheet
24	Silver metal	Cutting machine blade
25	Silver metal	Large hinge
26	Silver metal	Small hinge
27	Silver metal	Metal pourer
28	Silver metal	Rivet B(MO8293)
29	Silver metal	Rivet C(MO8293)
30	Silver metal	Bottle stopper head
31	Black foam	Base


To be continued



Zhejiang J-testing Service Co.,Ltd.


Add: West of 3/F, No.5 Building, No.968 Xuefeng West Road, Beiyuan Street, Yiwu, Zhejiang, China 322000
 Customer service: info@j-testing.com/+86 057985309611 Web: www.jts-cert.com

Sample Photos









31



23





25110355

*** End of Report ***



TEST REPORT

Report No.: JTS25110355-2ER1

Date: Dec. 03, 2025

Page 24 of 24

GENERAL CONDITIONS OF SERVICES

JTS Testing Services Co., Ltd. (hereinafter "JTS"), while reserving the right to decline, without giving any reason whatsoever, any request for the undertaking of a test or investigation, will carry out at the request of the clients the required test or investigation subject always to the following conditions:

1. JTS only acts for the person or body originating the instructions (the "Clients"). No other party is entitled to give instructions, particularly on the scope of testing or delivery of report or certificate, unless authorized by the Clients.
2. The Sample(s) to be tested or investigated shall be delivered at the costs of the Clients and in accordance with the requirements of JTS. Improper shipping, packaging, and labeling of the Sample(s) by the Client may result in incorrect testing results, JTS shall be under no obligation to the Clients. At the conclusion of the test or investigation, the Clients shall, if required by JTS, collect the Sample(s). In any event, if the Sample(s) are not collected by the Clients within 60 days from the issuance date of the test report (for perishable items such as food and water samples, the relevant period shall be the preserving period up to 30 days), JTS may at its discretion dispose of the Sample(s) without any compensation to the Clients.
3. The Clients shall always comply with the following before or during JTS providing its services:
 - a) provide sample(s) and relevant data, at the same time, guarantee the consistence of the sample(s) name they declared with the sample(s) or the goods provided. Otherwise, JTS will not bear any relevant responsibilities;
 - b) giving timely instructions and adequate information to enable JTS to perform the services effectively;
 - c) supply, when requested by JTS, any equipment and personnel for the performance of the services;
 - d) take all necessary steps to eliminate or remedy any obstruction in the performance of the services;
 - e) inform JTS in advance of any hazards or dangers, actual or potential, associated with any order of samples or testing;
 - f) provide all necessary access for JTS's representative to enable the required services to be performed effectively;
 - g) ensure all essential steps are taken for safety of working conditions, sites and installations during the performance of services;
 - h) fully discharge all its liabilities under any contract like sales contract with a third party, whether or not a report or certificate has been issued by JTS, failing which JTS shall be under no obligation to the Clients.
4. Subject to JTS's accepting the Client's instructions, JTS will issue reports or certificates which reflect statements of opinion made with due care within the scope of instructions but JTS is not obliged to report upon any facts outside the instructions, if there were any dissidence about the report or certificate, the Client should provide the written declaration to JTS within 30 days after the date receiving the report or certificate, otherwise, JTS will not hear the case after the date limit.
5. JTS is irrevocably authorized by the Clients to deliver at its discretion the report or the certificate to any third party when instructed by the Clients or where it implicitly follows from circumstances, trade custom, usage or practice as determined by JTS.
6. A test report will be issued in confidence to the Clients and it will be strictly treated as such by JTS. It may not be reproduced either in its entirety or in part and it may not be used for advertising or other unauthorized purposes without the written consent of JTS. The Clients to whom the Report is issued may, however, show or send it, or a certified copy thereof prepared by JTS, to his customer, supplier or other persons directly concerned. JTS will not, without the consent of the Clients, enter into any discussion or correspondence with any third party concerning the contents of the report unless required by the relevant governmental authorities, laws or court orders.
7. Applicants wishing to use JTS's reports in court proceedings or arbitration shall inform JTS to that effect prior to submitting the sample for testing.
8. The report will refer only to the sample tested and will not apply to the bulk, unless the sampling has been carried out by JTS and is stated as such in the Report. Also, the report is only for reference.
9. Any documents containing engagements between the Clients and third parties like contracts of sale, letters of credit, bills of lading, etc. are regarded as information for JTS only and do not affect the scope of the services or the obligations accepted by JTS.
10. If the Clients do not specify the methods/standards to be applied, JTS will choose the appropriate ones and further information regarding the methods can be obtained by direct contact with JTS, for the in-house method, JTS will only provide the summary.
11. No liability shall be incurred by and no claim shall be made against JTS or its servants, agents, employees or independent contractors in respect of any loss or damage to any such materials, equipment and property occurring whilst at JTS or any work places in which the testing is carried out, or in the course of transit to or from JTS or the said work places, whether or not resulting from any acts, neglect or default on the part of any such servants, agents, employees or independent contractors of JTS.
12. JTS will not be liable, or accept responsibility for any loss or damage howsoever arising from the use of information contained in any of its reports or in any communication whatsoever about its said tests or investigations.
13. Subject to Clause 11 and 12, the total liability of JTS in respect of any claim of loss, damage or expense of whatsoever nature shall not exceed a total sum equal to two times the amount of the service fee payable in respect of the services directly related to such claim, and JTS's liability shall not include any indirect, special or consequential loss of the Clients.
14. In the event of JTS prevented by any cause outside JTS's control from performing any service for which an order has been given or an agreement made, the Clients shall pay to JTS:
 - a) the amount of all abortive expenditure actually made or incurred;
 - b) a proportion of the agreed fee or commission equal to the proportion (if any) of the service actually carried out by JTS, and JTS shall be relieved of all responsibility whatsoever for the partial or total non-performance of the required service.
15. JTS shall be discharged from all liabilities for all claims for loss, damage or expense unless suit is brought within one calendar year after the date of the performance by JTS of the service relating to the claim or in the event of any alleged non-performance within one year of the date when such service should have been completed.
16. The Clients acknowledge that JTS does not, either by entering into a contract or by performing service, assume or undertake to discharge any duty of the Clients to any other persons. JTS is neither an insurer nor a guarantor and disclaims all liability in such capacity.
17. The Clients shall hold harmless and indemnify JTS and its officers, employees, agents or independent contractors against all claims made by any third party for loss, damage or expense of whatsoever nature including reasonable legal expenses relating to the performance or non-performance of any services to the extent that the aggregate of any such claims relating to any one service exceed the limits mentioned in Clause 13.
18. Any unauthorized alteration, forgery or falsification of the content or appearance of the report/certificate is unlawful and offenders may be prosecuted to the fullest extent of the law; in the event of improper use of the report, JTS reserves the right to withdraw it, and to adopt any other measures which may be appropriate.
19. Samples are deposited with and accepted by JTS on the basis that either they are insured by the Clients or the Clients assumes entire responsibility for loss through fire, theft, burglary or for damages arising in the course of analysis or handling, without recourse whatsoever to JTS or its servants, agents, employees or independent contractors.
20. If the requirements of the Clients require the analysis of sample by the Clients' or any third party's laboratory, JTS will only convey the result of the analysis without responsibility for its accuracy. If JTS is only able to witness an analysis by the Clients' or any third party's laboratory JTS will only confirm that the correct sample has been analyzed without responsibility for the accuracy of any analysis or results.
21. In the event of any unforeseen additional time or costs being incurred in the course of carrying out any of its services, JTS shall be entitled to charge the Clients additional fees to reflect the additional time and costs incurred.
22. All rights (including but not limited to copyright) in any reports, certificates or other materials produced by JTS in the course of providing its services shall remain vested in JTS.
23. Unless otherwise agreed in writing, payment is to be made within 10 days from the date of Invoice or the date of the Debit Note, all charges rendered by JTS or interest will become due at the rate of three percent per month from the date of invoice until actual payment. The Clients are also responsible for settling all JTS's costs of collecting the charges owed, including legal fees.
24. Test results may be transmitted by electronic means at the Client's request. However, it should be noted that electronic transmission cannot guarantee the information contained will not be lost, delayed or intercepted by third party. JTS is not liable for any disclosure, error or omission in the content of such messages as a result of electronic transmission.
25. If necessary, JTS may subcontract part or all tests to competent subcontractors. If no objection is raised at the time of the Clients submitting the application, JTS shall assume the Client's approval.
26. This report/certificate does not relieve sellers/suppliers from their contractual responsibility with regards to the quality/quantity of this delivery nor does it prejudice the Client's right to claim towards sellers/suppliers for compensation for any apparent and/or hidden defects not detected during JTS's random inspection or testing or audit.
27. JTS reserves the right to include Special Conditions in addition to the foregoing General Conditions if warranted by the particular circumstances of the required test or investigation [this clause is only effective when the other party has been informed.
28. The foregoing General Conditions shall in all respects be governed, construed, interpreted and operated in accordance with the relevant Chinese laws and regulations. Unless otherwise agreed, the arbitration shall take place in P. R. C.
29. These General Condition have been drafted in Chinese and may be translated into other languages. In the event of any discrepancy, the Chinese version shall prevail.
30. In general sample will be stored for 60 days. But for liquid, powder, etc semi-product & fragile product, it will be stored only for 30 days.
31. The data of project 11 is derived from the contract report numbered SZ2025110108-1E (STQ Testing Services Co., Ltd.).

Zhejiang J-testing Service Co., Ltd.

Add: West of 3/F, No.5 Building, No.968 Xuefeng West Road, Beiyuan Street, Yiwu, ZheJiang, China 322000
Customer service: info@j-testing.com/+86 057985309611 Web: www.jts-cert.com