



# TEST REPORT

Report No.: CCI260701331EN

Report Date: Jul. 24, 2026

Page 1 of 13

**Applicant** : Mid Ocean Brands B.V.

**Address** : Unit 711-716, 7/F., Tower A, 83 King Lam Street, Cheung Sha Wan, Kowloon, Hong Kong

(The following sample(s) was (were) submitted and identified by client as)

**Sample Name** : Double wall flask

**Model/Item No.** : MO2107

**Vendor Code** : 107978

**Test Period** : From Jul. 17, 2026 to Jul. 23, 2026

**Tests Conducted** : As requested by the applicant, for details refer to next page(s).

Signed for and on behalf of

Compliance Control Institute (Guangzhou) Co., Ltd.

Approved by: \_\_\_\_\_

Pascal SHI/Technical Director

Compliance Control Institute (Guangzhou) Co., Ltd.

Room 701, Building 2, No.89, Majun Street, Nansha District, Guangzhou,  
Guangdong, China  
Tel: +86-20-84900678 Fax: +86-20-84910993  
Email: cs@ccilab.com.cn Website: www.ccilab.com.cn

This report is governed by, and incorporates by reference, the General Terms and Conditions of Testing which could be obtained / consulted by request to CCI or via the webpage of Conditions of Testing in the official website: [www.ccilab.com.cn](http://www.ccilab.com.cn). Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. This report sets forth our findings solely respect to the client's request(s) and the test results are obtained just with the submitted sample identified herein. The test results set forth in this report are not indicative or representative of the quality or characteristics of the lot from which a test sample was taken or any similar or identical product unless specifically and expressly noted. This report can not be reproduced except in full, without prior written permission of CCI. Any unauthorized alteration, forgery or falsification of the content or appearance of this report is unlawful, and any offenders may be prosecuted to the fullest extent of the law.



# TEST REPORT

Report No.: CCI260701331EN

Report Date: Jul. 24, 2026

Page 2 of 13

## Executive Summary:

| No. | TESTED SAMPLES                            | STANDARD / REQUIREMENT                                                                                                                                                                                                                          | CONCLUSION |
|-----|-------------------------------------------|-------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|------------|
| 1   | Tested material(s) of submitted sample(s) | Entry 23 of Annex XVII to the REACH Regulation (EC)<br>No.1907/2006 - Cadmium (Cd)                                                                                                                                                              | PASS       |
| 2   | Tested material(s) of submitted sample(s) | Entry 50 of Annex XVII to the REACH Regulation (EC)<br>No.1907/2006 - Polycyclic-aromatic hydrocarbons (PAH)                                                                                                                                    | PASS       |
| 3   | Tested material(s) of submitted sample(s) | Entry 51&52 of Annex XVII to the REACH Regulation (EC)<br>No.1907/2006 - Phthalate                                                                                                                                                              | PASS       |
| 4   | Tested material(s) of submitted sample(s) | Entry 63 of Annex XVII to the REACH Regulation (EC)<br>No.1907/2006 - Lead (Pb)                                                                                                                                                                 | PASS       |
| 5   | Tested material(s) of submitted sample(s) | Regulation (EC) No. 1935/2004 and Technical guide on Metals and alloys used in food contact materials and articles (2 <sup>nd</sup> edition), supplementing Council of Europe Resolution CM/Res (2020)9<br>- Specific migration of heavy metals | PASS       |
| 6   | Tested material(s) of submitted sample(s) | Regulation (EC) No. 1935/2004 & Resolution AP(2004)5 on Silicone rubber products intended to come into contact with foodstuffs<br>- Overall Migration<br>- 3% Acetic acid<br>- 50% Ethanol<br>- Bisphenol A (BPA)                               | PASS       |
| 7   | Tested material(s) of submitted sample(s) | French Arrêté du 25 novembre 1992 on Silicon<br>- Overall Migration<br>- 3% Acetic acid<br>- 50% Ethanol<br>- Volatile Organic matter (VOM)<br>- Peroxide Value<br>- Specific migration of organotin (As Tin)<br>- Bisphenol A (BPA)            | PASS       |
| 8   | Tested material(s) of submitted sample(s) | Dishwasher safe test for complying with the requirements stated in the Clause 5.4 of PAS 54:2003                                                                                                                                                | PASS       |



# TEST REPORT

Report No.: CCI260701331EN

Report Date: Jul. 24, 2026

Page 3 of 13

## TESTS CONDUCTED:

### 1. Cadmium (Cd)

Test Method: With reference to EPA 3052:1996, EPA 3050B:1996, the analysis was performed by Atomic Absorption Spectroscopy (AAS) or Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

| Material No. | Limit (mg/kg) | RL (mg/kg) | Test Result (mg/kg) | Conclusion |
|--------------|---------------|------------|---------------------|------------|
| 5            | 100           | 2          | N.D.                | PASS       |
| 6+7+8        | 1000          | 2          | N.D.                | PASS       |

## Note:

1. mg/kg = Milligram per kilogram.
2. N.D. = Not Detected (< RL).
3. RL = Reporting Limit.

### 2. Polycyclic-aromatic hydrocarbons (PAH)

Test Method: With reference to AfPS GS 2019:01 PAK, the analysis was performed by Gas Chromatography-Mass Spectrometry (GC-MS).

| Restricted Substances          | CAS No.  | RL (mg/kg) | Test Result (mg/kg) |       |
|--------------------------------|----------|------------|---------------------|-------|
|                                |          |            | 5                   | 6+7+8 |
| Benzo[a]pyrene (BaP)           | 50-32-8  | 0.2        | N.D.                | N.D.  |
| Benzo[e]pyrene (BeP)           | 192-97-2 | 0.2        | N.D.                | N.D.  |
| Benzo[a]anthracene (BaA)       | 56-55-3  | 0.2        | N.D.                | N.D.  |
| Chrysen (CHR)                  | 218-01-9 | 0.2        | N.D.                | N.D.  |
| Benzo[b]fluoranthene (BbFA)    | 205-99-2 | 0.2        | N.D.                | N.D.  |
| Benzo[j]fluoranthene (BjFA)    | 205-82-3 | 0.2        | N.D.                | N.D.  |
| Benzo[k]fluoranthene (BkFA)    | 207-08-9 | 0.2        | N.D.                | N.D.  |
| Dibenzo[a,h]anthracene (DBAhA) | 53-70-3  | 0.2        | N.D.                | N.D.  |
| Conclusion                     |          |            | PASS                | PASS  |

## Note:

1. mg/kg = Milligram per kilogram.
2. N.D. = Not Detected (< RL).
3. RL = Reporting Limit.
4. Requirement: a) For articles for supply to the general public: No more than 1mg/kg each;  
b) For toys: No more than 0.5mg/kg each.



# TEST REPORT

Report No.: CCI260701331EN

Report Date: Jul. 24, 2026

Page 4 of 13

## 3. Phthalates

Test Method: With reference to EN 14372:2004, the analysis was performed by Gas Chromatography-Mass Spectrometry (GC-MS).

| Restricted Substances              | CAS No.                  | RL (%) | Limit (%) | Test Result (%) |       |
|------------------------------------|--------------------------|--------|-----------|-----------------|-------|
|                                    |                          |        |           | 5               | 6+7+8 |
| Bis(2-ethylhexyl) phthalate (DEHP) | 117-81-7                 | 0.003  | 0.1       | N.D.            | N.D.  |
| Dibutyl phthalate (DBP)            | 84-74-2                  | 0.003  | 0.1       | N.D.            | N.D.  |
| Benzyl butyl phthalate (BBP)       | 85-68-7                  | 0.003  | 0.1       | N.D.            | N.D.  |
| Diisobutyl phthalate (DIBP)        | 84-69-5                  | 0.003  | 0.1       | N.D.            | N.D.  |
| Sum                                |                          | /      | 0.1       | N.D.            | N.D.  |
| Di-isononyl phthalate (DINP)       | 28553-12-0<br>68515-48-0 | 0.005  | 0.1       | N.D.            | N.D.  |
| Di-isodecyl phthalate (DIDP)       | 26761-40-0<br>68515-49-1 | 0.005  | 0.1       | N.D.            | N.D.  |
| Di-n-octyl phthalate (DNOP)        | 117-84-0                 | 0.003  | 0.1       | N.D.            | N.D.  |
| Sum                                |                          | /      | 0.1       | N.D.            | N.D.  |
| Conclusion                         |                          |        |           | PASS            | N.D.  |

### Note:

1. % = Percentage by weight.
2. N.D. = Not Detected (< RL).
3. RL = Reporting Limit.
4. / = Not Specified.



# TEST REPORT

Report No.: CCI260701331EN

Report Date: Jul. 24, 2026

Page 5 of 13

## 4. Lead (Pb)

Test Method: With reference to EPA 3052:1996, EPA 3050B:1996, the analysis was performed by Atomic Absorption Spectroscopy (AAS) or Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

| Material No. | Limit (mg/kg) | RL (mg/kg) | Test Result (mg/kg) | Conclusion |
|--------------|---------------|------------|---------------------|------------|
| 1+2          | 500           | 2          | N.D.                | PASS       |
| 3+4          | 500           | 2          | N.D.                | PASS       |
| 5            | 500           | 2          | N.D.                | PASS       |
| 6+7+8        | 500           | 2          | N.D.                | PASS       |

### Note:

1. mg/kg = Milligram per kilogram.
2. N.D. = Not Detected (< RL).
3. RL = Reporting Limit.



# TEST REPORT

Report No.: CCI260701331EN

Report Date: Jul. 24, 2026

Page 6 of 13

## 5. Specific migration of heavy metal

Test Method: With reference to the Chapter 3 of the Technical guide on Metals and alloys used in food contact materials and articles (2nd edition), the analysis was performed by Atomic Absorption Spectrophotometer (AAS) or Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES) or Inductively Coupled Plasma Mass Spectrometer (ICP-MS).

Test Condition: 5g/L Citric acid, 70°C, 2h, 3 times release tests

| Test Item       | RL<br>(mg/kg) | Limit (mg/kg)                                    |                                 | Test Result (mg/kg)                              |                                 | Conclusion |
|-----------------|---------------|--------------------------------------------------|---------------------------------|--------------------------------------------------|---------------------------------|------------|
|                 |               |                                                  |                                 | 2                                                |                                 |            |
|                 |               | Migration of<br>1 <sup>st</sup> +2 <sup>nd</sup> | Migration of<br>3 <sup>rd</sup> | Migration of<br>1 <sup>st</sup> +2 <sup>nd</sup> | Migration of<br>3 <sup>rd</sup> |            |
| Aluminum (Al)   | 0.2           | 35                                               | 5                               | N.D.                                             | N.D.                            | PASS       |
| Antimony (Sb)   | 0.02          | 0.28                                             | 0.04                            | N.D.                                             | N.D.                            | PASS       |
| Chromium (Cr)   | 0.1           | 7                                                | 1                               | N.D.                                             | N.D.                            | PASS       |
| Cobalt (Co)     | 0.01          | 0.14                                             | 0.02                            | N.D.                                             | N.D.                            | PASS       |
| Copper (Cu)     | 0.2           | 28                                               | 4                               | N.D.                                             | N.D.                            | PASS       |
| Iron (Fe)       | 0.5           | 280                                              | 40                              | N.D.                                             | N.D.                            | PASS       |
| Magnesium (Mg)  | 1.0           | --                                               | --                              | N.D.                                             | N.D.                            | PASS       |
| Manganese (Mn)  | 0.2           | 3.85                                             | 0.55                            | N.D.                                             | N.D.                            | PASS       |
| Molybdenum (Mo) | 0.02          | 0.84                                             | 0.12                            | N.D.                                             | N.D.                            | PASS       |
| Nickel (Ni)     | 0.02          | 0.98                                             | 0.14                            | N.D.                                             | N.D.                            | PASS       |
| Silver (Ag)     | 0.02          | 0.56                                             | 0.08                            | N.D.                                             | N.D.                            | PASS       |
| Tin (Sn)        | 1.0           | 700                                              | 100                             | N.D.                                             | N.D.                            | PASS       |
| Ti(Titanium)    | 0.01          | --                                               | --                              | N.D.                                             | N.D.                            | PASS       |
| Vanadium (V)    | 0.005         | 0.07                                             | 0.01                            | N.D.                                             | N.D.                            | PASS       |
| Zinc (Zn)       | 1.0           | 35                                               | 5                               | N.D.                                             | N.D.                            | PASS       |
| Zirconium (Zr)  | 1.0           | 14                                               | 2                               | N.D.                                             | N.D.                            | PASS       |
| Arsenic (As)    | 0.001         | 0.014                                            | 0.002                           | N.D.                                             | N.D.                            | PASS       |
| Barium (Ba)     | 0.2           | 8.4                                              | 1.2                             | N.D.                                             | N.D.                            | PASS       |
| Beryllium (Be)  | 0.005         | 0.07                                             | 0.01                            | N.D.                                             | N.D.                            | PASS       |
| Cadmium (Cd)    | 0.002         | 0.035                                            | 0.005                           | N.D.                                             | N.D.                            | PASS       |
| Lead (Pb)       | 0.002         | 0.070                                            | 0.010                           | N.D.                                             | N.D.                            | PASS       |
| Lithium (Li)    | 0.01          | 0.336                                            | 0.048                           | N.D.                                             | N.D.                            | PASS       |
| Mercury (Hg)    | 0.002         | 0.021                                            | 0.003                           | N.D.                                             | N.D.                            | PASS       |
| Thallium (Tl)   | 0.001         | 0.007                                            | 0.001                           | N.D.                                             | N.D.                            | PASS       |



# TEST REPORT

Report No.: CCI260701331EN

Report Date: Jul. 24, 2026

Page 7 of 13

Test Condition: 5g/L Citric acid, 70°C, 2h, 3 times release tests

| Test Item       | RL<br>(mg/kg) | Limit (mg/kg)                                    |                                 | Test Result (mg/kg)                              |                                 | Conclusion |
|-----------------|---------------|--------------------------------------------------|---------------------------------|--------------------------------------------------|---------------------------------|------------|
|                 |               |                                                  |                                 | 3                                                |                                 |            |
|                 |               | Migration of<br>1 <sup>st</sup> +2 <sup>nd</sup> | Migration of<br>3 <sup>rd</sup> | Migration of<br>1 <sup>st</sup> +2 <sup>nd</sup> | Migration of<br>3 <sup>rd</sup> |            |
| Aluminum (Al)   | 0.2           | 35                                               | 5                               | N.D.                                             | N.D.                            | PASS       |
| Antimony (Sb)   | 0.02          | 0.28                                             | 0.04                            | N.D.                                             | N.D.                            | PASS       |
| Chromium (Cr)   | 0.1           | 7                                                | 1                               | N.D.                                             | N.D.                            | PASS       |
| Cobalt (Co)     | 0.01          | 0.14                                             | 0.02                            | N.D.                                             | N.D.                            | PASS       |
| Copper (Cu)     | 0.2           | 28                                               | 4                               | N.D.                                             | N.D.                            | PASS       |
| Iron (Fe)       | 0.5           | 280                                              | 40                              | N.D.                                             | N.D.                            | PASS       |
| Magnesium (Mg)  | 1.0           | --                                               | --                              | N.D.                                             | N.D.                            | PASS       |
| Manganese (Mn)  | 0.2           | 3.85                                             | 0.55                            | N.D.                                             | N.D.                            | PASS       |
| Molybdenum (Mo) | 0.02          | 0.84                                             | 0.12                            | N.D.                                             | N.D.                            | PASS       |
| Nickel (Ni)     | 0.02          | 0.98                                             | 0.14                            | N.D.                                             | N.D.                            | PASS       |
| Silver (Ag)     | 0.02          | 0.56                                             | 0.08                            | N.D.                                             | N.D.                            | PASS       |
| Tin (Sn)        | 1.0           | 700                                              | 100                             | N.D.                                             | N.D.                            | PASS       |
| Ti(Titanium)    | 0.01          | --                                               | --                              | N.D.                                             | N.D.                            | PASS       |
| Vanadium (V)    | 0.005         | 0.07                                             | 0.01                            | N.D.                                             | N.D.                            | PASS       |
| Zinc (Zn)       | 1.0           | 35                                               | 5                               | N.D.                                             | N.D.                            | PASS       |
| Zirconium (Zr)  | 1.0           | 14                                               | 2                               | N.D.                                             | N.D.                            | PASS       |
| Arsenic (As)    | 0.001         | 0.014                                            | 0.002                           | N.D.                                             | N.D.                            | PASS       |
| Barium (Ba)     | 0.2           | 8.4                                              | 1.2                             | N.D.                                             | N.D.                            | PASS       |
| Beryllium (Be)  | 0.005         | 0.07                                             | 0.01                            | N.D.                                             | N.D.                            | PASS       |
| Cadmium (Cd)    | 0.002         | 0.035                                            | 0.005                           | N.D.                                             | N.D.                            | PASS       |
| Lead (Pb)       | 0.002         | 0.070                                            | 0.010                           | N.D.                                             | N.D.                            | PASS       |
| Lithium (Li)    | 0.01          | 0.336                                            | 0.048                           | N.D.                                             | N.D.                            | PASS       |
| Mercury (Hg)    | 0.002         | 0.021                                            | 0.003                           | N.D.                                             | N.D.                            | PASS       |
| Thallium (Tl)   | 0.001         | 0.007                                            | 0.001                           | N.D.                                             | N.D.                            | PASS       |

## Note:

1. mg/kg = Milligram per kilogram.
2. N.D. = Not Detected (< RL).
3. RL = Reporting Limit.

Compliance Control Institute (Guangzhou) Co., Ltd.

Room 701, Building 2, No.89, Majun Street, Nansha District, Guangzhou,  
Guangdong, China  
Tel: +86-20-84900678 Fax: +86-20-84910993  
Email: cs@ccilab.com.cn Website: www.ccilab.com.cn

This report is governed by, and incorporates by reference, the General Terms and Conditions of Testing which could be obtained / consulted by request to CCI or via the webpage of Conditions of Testing in the official website: www.ccilab.com.cn. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. This report sets forth our findings solely respect to the client's request(s) and the test results are obtained just with the submitted sample identified herein. The test results set forth in this report are not indicative or representative of the quality or characteristics of the lot from which a test sample was taken or any similar or identical product unless specifically and expressly noted. This report can not be reproduced except in full, without prior written permission of CCI. Any unauthorized alteration, forgery or falsification of the content or appearance of this report is unlawful, and any offenders may be prosecuted to the fullest extent of the law.



# TEST REPORT

Report No.: CCI260701331EN

Report Date: Jul. 24, 2026

Page 8 of 13

## 6.1. Overall Migration

Test Method: With reference to EN 1186-1:2002, EN 1186-3:2022

S/V ratio: 1.16 dm<sup>2</sup> / 116 mL

| Simulant Used                                    | Limit<br>(mg/dm <sup>2</sup> ) | RL<br>(mg/dm <sup>2</sup> ) | Test Result     |                 |                 |
|--------------------------------------------------|--------------------------------|-----------------------------|-----------------|-----------------|-----------------|
|                                                  |                                |                             | 5               |                 |                 |
|                                                  |                                |                             | 1 <sup>st</sup> | 2 <sup>nd</sup> | 3 <sup>rd</sup> |
| Overall Migration - 3% Acetic acid<br>(70°C, 2h) | 10                             | 1                           | N.D.            | N.D.            | N.D.            |
| Overall Migration - 50% Ethanol<br>(70°C, 2h)    | 10                             | 1                           | N.D.            | N.D.            | N.D.            |
| Conclusion                                       |                                |                             | PASS            |                 |                 |

### Note:

1. mg/dm<sup>2</sup> = Milligram per square decimeter.
2. N.D. = Not Detected (< RL).
3. RL = Reporting Limit.

## 6.2. Bisphenol A (BPA)

Test Method: With reference to EPA 3550C:2007, the analysis was performed by Ultra High Performance Liquid Chromatography coupled with tandem Mass Spectrometry (UPLC-MS-MS).

| Material No. | Limit (µg/kg) | RL (µg/kg) | Test Result (µg/kg) | Conclusion |
|--------------|---------------|------------|---------------------|------------|
| 5            | N.D.          | 1          | N.D.                | PASS       |

### Note:

1. µg/kg = Microgram per kilogram.
2. N.D. = Not Detected (< RL).
3. RL = Reporting Limit.



# TEST REPORT

Report No.: CCI260701331EN

Report Date: Jul. 24, 2026

Page 9 of 13

## 7.1. Overall Migration

Test Method: With reference to the Annex III to Arrêté du 25 novembre 1992

S/V ration: 1.16 dm<sup>2</sup> / 116 mL

| Simulant Used                                    | Limit<br>(mg/dm <sup>2</sup> ) | RL<br>(mg/dm <sup>2</sup> ) | Test Result     |                 |                 |
|--------------------------------------------------|--------------------------------|-----------------------------|-----------------|-----------------|-----------------|
|                                                  |                                |                             | 5               |                 |                 |
|                                                  |                                |                             | 1 <sup>st</sup> | 2 <sup>nd</sup> | 3 <sup>rd</sup> |
| Overall Migration - 3% Acetic acid<br>(70°C, 2h) | 10                             | 1                           | N.D.            | N.D.            | N.D.            |
| Overall Migration - 50% Ethanol<br>(70°C, 2h)    | 10                             | 1                           | N.D.            | N.D.            | N.D.            |
| Conclusion                                       |                                |                             | PASS            |                 |                 |

### Note:

1. mg/dm<sup>2</sup> = Milligram per square decimeter.
2. N.D. = Not Detected (< RL).
3. RL = Reporting Limit.

## 7.2. Volatile organic matter (VOM)

Test Method: With reference to the Annex III to Arrêté du 25 novembre 1992

Test Condition: 200°C, 4h

| Material No. | Limit (%) | RL (%) | Test Result (%) | Conclusion |
|--------------|-----------|--------|-----------------|------------|
| 5            | 0.5       | 0.1    | 0.2             | PASS       |

### Note:

1. % = Percentage by weight.
2. N.D. = Not Detected (< RL).
3. RL = Reporting Limit.

## 7.3. Peroxide Value

Test Method: With reference to the French pharmacopeia, 9th edition

| Material No. | Limit    | Test Result | Conclusion |
|--------------|----------|-------------|------------|
| 5            | Negative | Negative    | PASS       |



# TEST REPORT

Report No.: CCI260701331EN

Report Date: Jul. 24, 2026

Page 10 of 13

## 7.4. Specific migration of organotin (As Tin)

Test Method: With reference to Kunststoffe im Lebensmittelverkehr, Part B II IX

| Test Item  | Limit (mg/kg) | RL (mg/kg) | Test Result (mg/kg) |
|------------|---------------|------------|---------------------|
|            |               |            | 5                   |
| Tin        | 0.1           | 0.1        | N.D.                |
| Conclusion |               |            | PASS                |

### Note:

1. mg/kg = Milligram per kilogram.
2. N.D. = Not Detected (< RL).
3. RL = Reporting Limit.

## 7.5. Bisphenol A (BPA)

Test Method: With reference to EPA 3550C:2007, the analysis was performed by Ultra High Performance Liquid Chromatography coupled with tandem Mass Spectrometry (UPLC-MS-MS).

| Material No. | Limit (µg/kg) | RL (µg/kg) | Test Result (µg/kg) | Conclusion |
|--------------|---------------|------------|---------------------|------------|
| 5            | Not Detected  | 1          | N.D.                | PASS       |

### Note:

1. µg/kg = Microgram per kilogram.
2. N.D. = Not Detected (< RL).
3. RL = Reporting Limit.



# TEST REPORT

Report No.: CCI260701331EN

Report Date: Jul. 24, 2026

Page 11 of 13

## 8. Dishwasher safe test

Test Method: With reference to EN12875-1:2005

Number of cycles: 10

| Material No.        | 9      |   |   |       |   |   |          |   |   |                                                       |   |   |
|---------------------|--------|---|---|-------|---|---|----------|---|---|-------------------------------------------------------|---|---|
| Triplicate          | A      | B | C | A     | B | C | A        | B | C | A                                                     | B | C |
| Inspection criteria | Color* |   |   | Gloss |   |   | Clouding |   |   | Resistant deposits and iridescent layers <sup>#</sup> |   |   |
| Inspector 1         | 0      | 0 | 0 | 0     | 0 | 0 | 0        | 0 | 0 | 0                                                     | 0 | 0 |
| Inspector 2         | 0      | 0 | 0 | 0     | 0 | 0 | 0        | 0 | 0 | 0                                                     | 0 | 0 |
| Average Value       | 0      |   |   | 0     |   |   | 0        |   |   | 0                                                     |   |   |

### Remark:

- 1, \* = If several colors are present on one article to be inspected, the color with the greatest change shall be chosen.
- 2, # = For the elimination of easily removable deposits.

### Evaluation of inspection criteria:

| Classification | Rating                   |
|----------------|--------------------------|
| 0              | No visible change        |
| 1              | First discernible change |
| 2              | Clearly visible change   |

### Note:

- 1, Sample photos are for reference only. Actual colors of the photos may vary due to lighting and output process.
  - 2, Requirements quoted from the Clause 5.4 of the Publicly Available Specification PAS 54: 2003
- Articles that are designated "dishwasher resistant", "dishwasher proof", "dishwasher safe" or any other similar description that suggests that the articles can be safely cleaned in a dishwasher shall, on average, either show no visible change compared with untreated tableware (Classification 0) or show very slightly visible change (Classification 1) but shall not show clearly visible change (Classification 2).



# TEST REPORT

Report No.: CCI260701331EN

Report Date: Jul. 24, 2026

Page 12 of 13

## Test Material(s) List

| Material No. | Description          | Location       | Material        |
|--------------|----------------------|----------------|-----------------|
| 1            | Silver metal         | Handle         | /               |
| 2            | Silver metal         | Cover          | Stainless steel |
| 3            | Silvery metal        | Flask interior | Stainless steel |
| 4            | Silvery metal        | Flask exterior | /               |
| 5            | Transparent silicone | Sealing ring   | Silicone        |
| 6            | Black coating        | Flask body     | /               |
| 7            | Orange coating       | Flask body     | /               |
| 8            | Fuchsia coating      | Flask body     | /               |
| 9            | Whole product-Black  | /              | /               |



# TEST REPORT

Report No.: CCI260701331EN

Report Date: Jul. 24, 2026

Page 13 of 13

## Photo Appendix



## Additional Photo Appendix



★★★★★End of Report★★★★★