



TEST REPORT

Report No.: CCI260701683EN

Report Date: Aug. 12, 2026

Page 1 of 16

Applicant : Mid Ocean Brands B.V.

Address : Unit 711-716, 7/F., Tower A, 83 King Lam Street, Cheung Sha Wan, Kowloon, Hong Kong

(The following sample(s) was (were) submitted and identified by client as)

Sample Name : Double wall flask

Model/Item No. : MO6288

Vendor Code : 107978

Test Period : From Jul. 28, 2026 to Jul. 31, 2026

Tests Conducted : As requested by the applicant, for details refer to next page(s).

Signed for and on behalf of

Compliance Control Institute (Guangzhou) Co., Ltd.

Approved by: _____

Pascal SHI/Technical Director

Compliance Control Institute (Guangzhou) Co., Ltd.

Room 701, Building 2, No.89, Majun Street, Nansha District, Guangzhou,
Guangdong, China
Tel: +86-20-84900678 Fax: +86-20-84910993
Email: cs@ccilab.com.cn Website: www.ccilab.com.cn

This report is governed by, and incorporates by reference, the General Terms and Conditions of Testing which could be obtained / consulted by request to CCI or via the webpage of Conditions of Testing in the official website: www.ccilab.com.cn. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues identified therein. This test sets forth our findings solely respect to the client's request(s) and the test results are obtained just with the submitted sample identified herein. The test results set forth in this report are not indicative or representative of the quality or characteristics of the lot from which a test sample was taken or any similar or identical product unless specifically and expressly noted. This report can not be reproduced except in full, without prior written permission of CCI. Any unauthorized alteration, forgery or falsification of the content or appearance of this report is unlawful, and any offenders may be prosecuted to the fullest extent of the law.



TEST REPORT

Report No.: CCI260701683EN

Report Date: Aug. 12, 2026

Page 2 of 16

Executive Summary:

No.	TESTED SAMPLES	STANDARD / REQUIREMENT	CONCLUSION
1	Tested material(s) of submitted sample(s)	Entry 23 of Annex XVII to the REACH Regulation (EC) No.1907/2006 - Cadmium (Cd)	PASS
2	Tested material(s) of submitted sample(s)	Entry 50 of Annex XVII to the REACH Regulation (EC) No.1907/2006 - Polycyclic-aromatic hydrocarbons (PAH)	PASS
3	Tested material(s) of submitted sample(s)	Entry 51&52 of Annex XVII to the REACH Regulation (EC) No.1907/2006 - Phthalate	PASS
4	Tested material(s) of submitted sample(s)	Entry 63 of Annex XVII to the REACH Regulation (EC) No.1907/2006 - Lead (Pb)	PASS
5	Tested material(s) of submitted sample(s)	Regulation (EC) No. 1935/2004 and Technical guide on Metals and alloys used in food contact materials and articles (2 nd edition), supplementing Council of Europe Resolution CM/Res (2020)9 - Specific migration of heavy metals	PASS
6	Tested material(s) of submitted sample(s)	Regulation (EC) No. 1935/2004 & Regulation (EU) No 10/2011 and amendment directive (EU) 2020/1245 and the amendment Commission Regulation (EU) 2024/3190 for plastic materials - Overall Migration - 3% Acetic acid - 50% Ethanol - Specific migration of restricted substances - Specific migration of Primary Aromatic Amines - Bisphenol A (BPA)	PASS
7	Tested material(s) of submitted sample(s)	Regulation (EC) No. 1935/2004 & Resolution AP(2004)5 on Silicone rubber products intended to come into contact with foodstuffs - Overall Migration - 3% Acetic acid - 50% Ethanol - Bisphenol A (BPA)	PASS
8	Tested material(s) of submitted sample(s)	French Arrêté du 25 novembre 1992 on Silicon - Overall Migration - 3% Acetic acid - 50% Ethanol - Volatile Organic matter (VOM) - Peroxide Value - Specific migration of organotin (As Tin) - Bisphenol A (BPA)	PASS



TEST REPORT

Report No.: CCI260701683EN

Report Date: Aug. 12, 2026

Page 3 of 16

9	Tested material(s) of submitted sample(s)	Dishwasher safe test for complying with the requirements stated in the Clause 5.4 of PAS 5 4:2003	PASS
---	---	---	------



TEST REPORT

Report No.: CCI260701683EN

Report Date: Aug. 12, 2026

Page 4 of 16

TESTS CONDUCTED:

1. Cadmium (Cd)

Test Method: With reference to EPA 3052:1996, EPA 3050B:1996, the analysis was performed by Atomic Absorption Spectroscopy (AAS) or Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

Material No.	Limit (mg/kg)	RL (mg/kg)	Test Result (mg/kg)	Conclusion
1+2	1000	2	N.D.	PASS
3+4	1000	2	N.D.	PASS
6	100	2	N.D.	PASS
7	100	2	N.D.	PASS

Note:

1. mg/kg = Milligram per kilogram.
2. N.D. = Not Detected (< RL).
3. RL = Reporting Limit.

2. Polycyclic-aromatic hydrocarbons (PAH)

Test Method: With reference to AfPS GS 2019:01 PAK, the analysis was performed by Gas Chromatography-Mass Spectrometry (GC-MS).

Restricted Substances	CAS No.	RL (mg/kg)	Test Result (mg/kg)			
			1+2	3+4	6	7
Benzo[a]pyrene (BaP)	50-32-8	0.2	N.D.	N.D.	N.D.	N.D.
Benzo[e]pyrene (BeP)	192-97-2	0.2	N.D.	N.D.	N.D.	N.D.
Benzo[a]anthracene (BaA)	56-55-3	0.2	N.D.	N.D.	N.D.	N.D.
Chrysen (CHR)	218-01-9	0.2	N.D.	N.D.	N.D.	N.D.
Benzo[b]fluoranthene (BbFA)	205-99-2	0.2	N.D.	N.D.	N.D.	N.D.
Benzo[j]fluoranthene (BjFA)	205-82-3	0.2	N.D.	N.D.	N.D.	N.D.
Benzo[k]fluoranthene (BkFA)	207-08-9	0.2	N.D.	N.D.	N.D.	N.D.
Dibenzo[a,h]anthracene (DBAhA)	53-70-3	0.2	N.D.	N.D.	N.D.	N.D.
Conclusion			PASS	PASS	PASS	PASS

Note:

1. mg/kg = Milligram per kilogram.
2. N.D. = Not Detected (< RL).
3. RL = Reporting Limit.
4. Requirement: a) For articles for supply to the general public: No more than 1mg/kg each;
b) For toys: No more than 0.5mg/kg each.



TEST REPORT

Report No.: CCI260701683EN

Report Date: Aug. 12, 2026

Page 5 of 16

3. Phthalates

Test Method: With reference to EN 14372:2004, the analysis was performed by Gas Chromatography-Mass Spectrometry (GC-MS).

Restricted Substances	CAS No.	RL (%)	Limit (%)	Test Result (%)			
				1+2	3+4	6	7
Bis(2-ethylhexyl) phthalate (DEHP)	117-81-7	0.003	0.1	N.D.	N.D.	N.D.	N.D.
Dibutyl phthalate (DBP)	84-74-2	0.003	0.1	N.D.	N.D.	N.D.	N.D.
Benzyl butyl phthalate (BBP)	85-68-7	0.003	0.1	N.D.	N.D.	N.D.	N.D.
Diisobutyl phthalate (DIBP)	84-69-5	0.003	0.1	N.D.	N.D.	N.D.	N.D.
Sum		/	0.1	N.D.	N.D.	N.D.	N.D.
Di-isononyl phthalate (DINP)	28553-12-0 68515-48-0	0.005	0.1	N.D.	N.D.	N.D.	N.D.
Di-isodecyl phthalate (DIDP)	26761-40-0 68515-49-1	0.005	0.1	N.D.	N.D.	N.D.	N.D.
Di-n-octyl phthalate (DNOP)	117-84-0	0.003	0.1	N.D.	N.D.	N.D.	N.D.
Sum		/	0.1	N.D.	N.D.	N.D.	N.D.
Conclusion				PASS	PASS	PASS	PASS

Note:

1. % = Percentage by weight.
2. N.D. = Not Detected (< RL).
3. RL = Reporting Limit.
4. / = Not Specified.



TEST REPORT

Report No.: CCI260701683EN

Report Date: Aug. 12, 2026

Page 6 of 16

4. Lead (Pb)

Test Method: With reference to EPA 3052:1996, EPA 3050B:1996, the analysis was performed by Atomic Absorption Spectroscopy (AAS) or Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

Material No.	Limit (mg/kg)	RL (mg/kg)	Test Result (mg/kg)	Conclusion
1+2	500	2	N.D.	PASS
3+4	500	2	N.D.	PASS
6	500	2	N.D.	PASS
7	500	2	N.D.	PASS
5+8+9	500	2	N.D.	PASS

Note:

1. mg/kg = Milligram per kilogram.
2. N.D. = Not Detected (< RL).
3. RL = Reporting Limit.



TEST REPORT

Report No.: CCI260701683EN

Report Date: Aug. 12, 2026

Page 7 of 16

5. Specific migration of heavy metal

Test Method: With reference to the Chapter 3 of the Technical guide on Metals and alloys used in food contact materials and articles (2nd edition), the analysis was performed by Atomic Absorption Spectrophotometer (AAS) or Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES) or Inductively Coupled Plasma Mass Spectrometer (ICP-MS).

Test Condition: 5g/L Citric acid, 70°C, 2h, 3 times release tests

Test Item	RL (mg/kg)	Limit (mg/kg)		Test Result (mg/kg)		Conclusion
				9		
		Migration of 1 st +2 nd	Migration of 3 rd	Migration of 1 st +2 nd	Migration of 3 rd	
Aluminum (Al)	0.2	35	5	N.D.	N.D.	PASS
Antimony (Sb)	0.02	0.28	0.04	N.D.	N.D.	PASS
Chromium (Cr)	0.1	7	1	N.D.	N.D.	PASS
Cobalt (Co)	0.01	0.14	0.02	N.D.	N.D.	PASS
Copper (Cu)	0.2	28	4	N.D.	N.D.	PASS
Iron (Fe)	0.5	280	40	N.D.	N.D.	PASS
Magnesium (Mg)	1.0	--	--	N.D.	N.D.	PASS
Manganese (Mn)	0.2	3.85	0.55	N.D.	N.D.	PASS
Molybdenum (Mo)	0.02	0.84	0.12	N.D.	N.D.	PASS
Nickel (Ni)	0.02	0.98	0.14	N.D.	N.D.	PASS
Silver (Ag)	0.02	0.56	0.08	N.D.	N.D.	PASS
Tin (Sn)	1.0	700	100	N.D.	N.D.	PASS
Ti(Titanium)	0.01	--	--	N.D.	N.D.	PASS
Vanadium (V)	0.005	0.07	0.01	N.D.	N.D.	PASS
Zinc (Zn)	1.0	35	5	N.D.	N.D.	PASS
Zirconium (Zr)	1.0	14	2	N.D.	N.D.	PASS
Arsenic (As)	0.001	0.014	0.002	N.D.	N.D.	PASS
Barium (Ba)	0.2	8.4	1.2	N.D.	N.D.	PASS
Beryllium (Be)	0.005	0.07	0.01	N.D.	N.D.	PASS
Cadmium (Cd)	0.002	0.035	0.005	N.D.	N.D.	PASS
Lead (Pb)	0.002	0.070	0.010	N.D.	N.D.	PASS
Lithium (Li)	0.01	0.336	0.048	N.D.	N.D.	PASS
Mercury (Hg)	0.002	0.021	0.003	N.D.	N.D.	PASS
Thallium (Tl)	0.001	0.007	0.001	N.D.	N.D.	PASS



TEST REPORT

Report No.: CCI260701683EN

Report Date: Aug. 12, 2026

Page 8 of 16

Note:

1. mg/kg = Milligram per kilogram.
2. N.D. = Not Detected (< RL).
3. RL = Reporting Limit.

6.1. Overall Migration

Test Method: With reference to EN 1186-1:2002, EN 1186-3:2022

S/V ration: 2.09dm²/209mL

Simulant Used	Limit (mg/dm ²)	RL (mg/dm ²)	Test Result		
			6		
			1 st	2 nd	3 rd
Overall Migration - 3% Acetic acid (70°C, 2h)	10	1	N.D.	N.D.	N.D.
Overall Migration - 50% Ethanol (70°C, 2h)	10	1	N.D.	N.D.	N.D.
Conclusion			PASS		

Note:

1. mg/dm² = Milligram per square decimeter.
2. N.D. = Not Detected (< RL).
3. RL = Reporting Limit.



TEST REPORT

Report No.: CCI260701683EN

Report Date: Aug. 12, 2026

Page 9 of 16

6.2. Specific migration of restricted substances

Test Method: EN 13130-1:2004, the analysis was performed by Inductively Coupled Plasma Mass Spectrometer (ICP-MS) or Inductively Coupled Plasma-Optical Emission Spectrometer (ICP-OES).

Test Condition: 3% acetic acid, 70°C, 2h

S/V ratio: 1.05 dm²/175 mL

Test Item	Limit (mg/kg)	RL (mg/kg)	Test Result (mg/kg)		
			6		
			1 st	2 nd	3 rd
Aluminum (Al)	1	0.05	N.D.	N.D.	N.D.
Manganese (Mn)	0.6	0.05	N.D.	N.D.	N.D.
Iron (Fe)	48	0.05	N.D.	N.D.	N.D.
Cobalt (Co)	0.05	0.01	N.D.	N.D.	N.D.
Copper (Cu)	5	0.05	N.D.	N.D.	N.D.
Zinc (Zn)	5	0.1	N.D.	N.D.	N.D.
Barium (Ba)	1	0.05	N.D.	N.D.	N.D.
Nickel (Ni)	0.02	0.01	N.D.	N.D.	N.D.
Lithium (Li)	0.6	0.02	N.D.	N.D.	N.D.
Antimony (Sb)	0.04	0.01	N.D.	N.D.	N.D.
Arsenic (As)	N.D.	0.01	N.D.	N.D.	N.D.
Cadmium (Cd)	N.D.	0.002	N.D.	N.D.	N.D.
Calcium (Ca)	/	0.01	N.D.	N.D.	N.D.
Chromium (Cr)	N.D.	0.01	N.D.	N.D.	N.D.
Europium (Eu)	0.05	0.05	N.D.	N.D.	N.D.
Gadolinium (Gd)	0.05	0.05	N.D.	N.D.	N.D.
Lanthanum (La)	0.05	0.05	N.D.	N.D.	N.D.
Lead (Pb)	N.D.	0.01	N.D.	N.D.	N.D.
Magnesium (Mg)	/	0.01	N.D.	N.D.	N.D.
Mercury (Hg)	N.D.	0.01	N.D.	N.D.	N.D.
Potassium (K)	/	0.01	N.D.	N.D.	N.D.
Sodium (Na)	/	0.01	N.D.	N.D.	N.D.
Terbium (Tb)	0.05	0.05	N.D.	N.D.	N.D.
Conclusion			PASS		

Note:

1. mg/kg = Milligram per kilogram.
2. N.D. = Not Detected (< RL).
3. RL = Reporting Limit.

Compliance Control Institute (Guangzhou) Co., Ltd.

Room 701, Building 2, No.89, Majun Street, Nansha District, Guangzhou, Guangdong, China
Tel: +86-20-84900678 Fax: +86-20-84910993
Email: cs@ccilab.com.cn Website: www.ccilab.com.cn

This report is governed by, and incorporates by reference, the General Terms and Conditions of Testing which could be obtained / consulted by request to CCI or via the webpage of Conditions of Testing in the official website: www.ccilab.com.cn. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. This report sets forth our findings solely respect to the client's request(s) and the test results are obtained just with the submitted sample identified herein. The test results set forth in this report are not indicative or representative of the quality or characteristics of the lot from which a test sample was taken or any similar or identical product unless specifically and expressly noted. This report can not be reproduced except in full, without prior written permission of CCI. Any unauthorized alteration, forgery or falsification of the content or appearance of this report is unlawful, and any offenders may be prosecuted to the fullest extent of the law.



TEST REPORT

Report No.: CCI260701683EN

Report Date: Aug. 12, 2026

Page 10 of 16

6.3. Specific migration of Primary Aromatic Amines Test Method: With reference to EN 13130-1:2004

Test Condition: 3% acetic acid, 70°C, 2h

S/V ratio: 1.05 dm²/175 mL

No.	Test Item	CAS No.	Limit (mg/kg)	RL (mg/kg)	Test Result (mg/kg)	Conclusion
					6	
1	4-aminodiphenyl	92-67-1	N.D.	0.002	N.D.	PASS
2	Benzidine	92-87-5	N.D.	0.002	N.D.	PASS
3	4-chloro-o-toluidine	95-69-2	N.D.	0.002	N.D.	PASS
4	2-naphthylamine	91-59-8	N.D.	0.002	N.D.	PASS
5	o-aminoazotoluene	97-56-3	N.D.	0.002	N.D.	PASS
6	2-amino-4-nitrotoluene	99-55-8	N.D.	0.002	N.D.	PASS
7	p-chloroaniline	106-47-8	N.D.	0.002	N.D.	PASS
8	2,4-diaminoanisole	615-05-4	N.D.	0.002	N.D.	PASS
9	4,4'-diaminodiphenylmethane	101-77-9	N.D.	0.002	N.D.	PASS
10	3,3'-dichlorobenzidine	91-94-1	N.D.	0.002	N.D.	PASS
11	3,3'-dimethoxybenzidine	119-90-4	N.D.	0.002	N.D.	PASS
12	3,3'-dimethylbenzidine	119-93-7	N.D.	0.002	N.D.	PASS
13	3,3'-dimethyl- 4,4'-diaminodiphenylmethane	838-88-0	N.D.	0.002	N.D.	PASS
14	p-cresidine	120-71-8	N.D.	0.002	N.D.	PASS
15	4,4'-methylene-bis-(2-chloroaniline)	101-14-4	N.D.	0.002	N.D.	PASS
16	4,4'-oxydianiline	101-80-4	N.D.	0.002	N.D.	PASS
17	4,4'-thiodianiline	139-65-1	N.D.	0.002	N.D.	PASS
18	o-toluidine	95-53-4	N.D.	0.002	N.D.	PASS
19	2,4-diaminotoluene	95-80-7	N.D.	0.002	N.D.	PASS
20	2,4,5-trimethylaniline	137-17-7	N.D.	0.002	N.D.	PASS
21	2-methoxyaniline	90-04-0	N.D.	0.002	N.D.	PASS
22	4-aminoazobenzene	60-09-3	N.D.	0.002	N.D.	PASS
Other primary aromatic amines (sum)			0.01	/	N.D.	PASS
23	1,4-Phenylenediamine	106-50-3	/	0.002	N.D.	PASS
24	1,3-Phenylenediamine	108-45-2	/	0.002	N.D.	PASS
25	Aniline	62-53-3	/	0.002	N.D.	PASS
26	2,6-Dimethylaniline (2,6-DMA)	87-62-7	/	0.002	N.D.	PASS
27	2,4'-Diaminodiphenylmethane	1208-52-2	/	0.002	N.D.	PASS
28	2,4-Dimethylaniline (2,4-DMA)	95-68-1	/	0.002	N.D.	PASS
29	2,2'-Methylenedianiline	6582-52-1	/	0.002	N.D.	PASS

Compliance Control Institute (Guangzhou) Co., Ltd.

Room 701, Building 2, No.89, Majun Street, Nansha District, Guangzhou,
Guangdong, China
Tel: +86-20-84900678 Fax: +86-20-84910993
Email: cs@ccilab.com.cn Website: www.ccilab.com.cn

This report is governed by, and incorporates by reference, the General Terms and Conditions of Testing which could be obtained / consulted by request to CCI or via the webpage of Conditions of Testing in the official website: www.ccilab.com.cn. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. This report sets forth our findings solely respect to the client's request(s) and the test results are obtained just with the submitted sample identified herein. The test results set forth in this report are not indicative or representative of the quality or characteristics of the lot from which a test sample was taken or any similar or identical product unless specifically and expressly noted. This report can not be reproduced except in full, without prior written permission of CCI. Any unauthorized alteration, forgery or falsification of the content or appearance of this report is unlawful, and any offenders may be prosecuted to the fullest extent of the law.



TEST REPORT

Report No.: CCI260701683EN

Report Date: Aug. 12, 2026

Page 11 of 16

Note:

1. mg/kg = Milligram per kilogram.
2. N.D. = Not Detected (< RL).
3. RL = Reporting Limit.

6.4. Bisphenol A (BPA)

Test Method: With reference to EPA 3550C:2007, the analysis was performed by Ultra High Performance Liquid Chromatography coupled with tandem Mass Spectrometry (UPLC-MS-MS).

Material No.	Limit (µg/kg)	RL (µg/kg)	Test Result (µg/kg)	Conclusion
6	Not Detected	1	N.D.	PASS

Note:

1. µg/kg = Microgram per kilogram.
2. N.D. = Not Detected (< RL).
3. RL = Reporting Limit.

7.1. Overall Migration

Test Method: With reference to EN 1186-1:2002, EN 1186-3:2022

S/V ration: 1.10 dm²/110 mL

Simulant Used	Limit (mg/dm ²)	RL (mg/dm ²)	Test Result		
			7		
			1 st	2 nd	3 rd
Overall Migration - 3% Acetic acid (70°C, 2h)	10	1	N.D.	N.D.	N.D.
Overall Migration - 50% Ethanol (70°C, 2h)	10	1	N.D.	N.D.	N.D.
Conclusion			PASS		

Note:

1. mg/dm² = Milligram per square decimeter.
2. N.D. = Not Detected (< RL).
3. RL = Reporting Limit.



TEST REPORT

Report No.: CCI260701683EN

Report Date: Aug. 12, 2026

Page 12 of 16

7.2. Bisphenol A (BPA)

Test Method: With reference to EPA 3550C:2007, the analysis was performed by Ultra High Performance Liquid Chromatography coupled with tandem Mass Spectrometry (UPLC-MS-MS).

Material No.	Limit (µg/kg)	RL (µg/kg)	Test Result (µg/kg)	Conclusion
7	Not Detected	1	N.D.	PASS

Note:

1. µg/kg = Microgram per kilogram.
2. N.D. = Not Detected (< RL).
3. RL = Reporting Limit.

8.1. Overall Migration

Test Method: With reference to the Annex III to Arrêté du 25 novembre 1992

S/V ration: 1.10 dm²/110 mL

Simulant Used	Limit (mg/dm ²)	RL (mg/dm ²)	Test Result		
			7		
			1 st	2 nd	3 rd
Overall Migration - 3% Ethanol (70°C, 2h)	10	1	N.D.	N.D.	N.D.
Overall Migration - 50% Ethanol (70°C, 2h)	10	1	N.D.	N.D.	N.D.
Conclusion			PASS		

Note:

1. mg/dm² = Milligram per square decimeter.
2. N.D. = Not Detected (< RL).
3. RL = Reporting Limit.

8.2. Volatile organic matter (VOM)

Test Method: With reference to the Annex III to Arrêté du 25 novembre 1992

Test Condition: 200°C, 4h

Material No.	Limit (%)	RL (%)	Test Result (%)	Conclusion
7	0.5	0.1	0.2	PASS



TEST REPORT

Report No.: CCI260701683EN

Report Date: Aug. 12, 2026

Page 13 of 16

Note:

1. % = Percentage by weight.
2. N.D. = Not Detected (< RL).
3. RL = Reporting Limit.

8.3. Peroxide Value

Test Method: With reference to the French pharmacopeia, 9th edition

Material No.	Limit	Test Result	Conclusion
7	Negative	Negative	PASS

Note:

1. % = Percentage by weight.
2. N.D. = Not Detected (< RL).
3. RL = Reporting Limit.

8.4. Specific migration of organotin (As Tin)

Test Method: With reference to Kunststoffe im Lebensmittelverkehr, Part B II IX

Test Item	Limit (mg/kg)	RL (mg/kg)	Test Result (mg/kg)
			7
Tin	0.1	0.1	N.D.
Conclusion			PASS

Note:

1. mg/kg = Milligram per kilogram.
2. N.D. = Not Detected (< RL).
3. RL = Reporting Limit.

8.5. Bisphenol A (BPA)

Test Method: With reference to EPA 3550C:2007, the analysis was performed by Ultra High Performance Liquid Chromatography coupled with tandem Mass Spectrometry (UPLC-MS-MS).

Material No.	Limit (µg/kg)	RL (µg/kg)	Test Result (µg/kg)	Conclusion
7	Not Detected	1	N.D.	PASS

Note:

1. mg/kg = Milligram per kilogram.

Compliance Control Institute (Guangzhou) Co., Ltd.

Room 701, Building 2, No.89, Majun Street, Nansha District, Guangzhou, Guangdong, China
Tel: +86-20-84900678 Fax: +86-20-84910993
Email: cs@ccilab.com.cn Website: www.ccilab.com.cn

This report is governed by, and incorporates by reference, the General Terms and Conditions of Testing which could be obtained / consulted by request to CCI or via the webpage of Conditions of Testing in the official website: www.ccilab.com.cn. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues identified therein. This report sets forth our findings solely respect to the client's request(s) and the test results are obtained just with the submitted sample identified herein. The test results set forth in this report are not indicative or representative of the quality or characteristics of the lot from which a test sample was taken or any similar or identical product unless specifically and expressly noted. This report can not be reproduced except in full, without prior written permission of CCI. Any unauthorized alteration, forgery or falsification of the content or appearance of this report is unlawful, and any offenders may be prosecuted to the fullest extent of the law.



TEST REPORT

Report No.: CCI260701683EN

Report Date: Aug. 12, 2026

Page 14 of 16

2. N.D. = Not Detected (< RL).

3. RL = Reporting Limit.

9. Dishwasher safe test

Test Method: With reference to EN12875-1:2005

Number of cycles: 10

Material No.	10											
Triplicate	A	B	C	A	B	C	A	B	C	A	B	C
Inspection criteria	Color*			Gloss			Clouding			Resistant deposits and iridescent layers#		
Inspector 1	0	0	0	0	0	0	0	0	0	0	0	0
Inspector 2	0	0	0	0	0	0	0	0	0	0	0	0
Average Value	0			0			0			0		

Remark:

1, * = If several colors are present on one article to be inspected, the color with the greatest change shall be chosen.

2, # = For the elimination of easily removable deposits.

Evaluation of inspection criteria:

Classification	Rating
0	No visible change
1	First discernible change
2	Clearly visible change

Note:

1, Sample photos are for reference only. Actual colors of the photos may vary due to lighting and output process.

2, Requirements quoted from the Clause 5.4 of the Publicly Available Specification PAS 54: 2003 Articles that are designated "dishwasher resistant", "dishwasher proof", "dishwasher safe" or any other similar description that suggests that the articles can be safely cleaned in a dishwasher shall, on average, either show no visible change compared with untreated tableware (Classification 0) or show very slightly visible change (Classification 1) but shall not show clearly visible change (Classification 2).



TEST REPORT

Report No.: CCI260701683EN

Report Date: Aug. 12, 2026

Page 15 of 16

Test Material(s) List

Material No.	Description	Location	Material
1	Black coating	Flask body	/
2	White coating	Flask body	/
3	Deep blue coating	Flask body	/
4	Light brown coating	Lid	/
5	Silvery metal	Lid	/
6	Black plastic	Lid	PP
7	Translucent silicone	Sealing ring	Silicone
8	Silvery metal	Flask exterior	/
9	Silvery metal	Flask interior	Stainless steel
10	Whole product - Deep blue	/	/



TEST REPORT

Report No.: CCI260701683EN

Report Date: Aug. 12, 2026

Page 16 of 16

Photo Appendix



Additional Photo Appendix



★★★★★End of Report★★★★★